

SRI LANKA STANDARD 1357 : 2008
ISO 105 – C10 : 2006

**METHODS FOR THE DETERMINATION
OF COLOUR FASTNESS OF TEXTILE
MATERIALS TO WASHING WITH SOAP
OR SOAP AND SODA**

SRI LANKA STANDARDS INSTITUTION

SRI LANKA STANDARD
METHODS FOR THE DETERMINATION OF COLOUR FASTNESS OF
TEXTILE MATERIALS TO WASHING WITH SOAP OR SOAP AND SODA

SLS 1357 : 2008
ISO 105 – C10 : 2006
(Superseding SLS 52:1998, SLS 53:1998, SLS 54:1998, SLS 55:1998
and SLS 56:1998)

Gr. C

SRI LANKA STANDARDS INSTITUTION
17 Victoria Place
Elvitigala Mawatha
Colombo 8
SRI LANKA.

Sri Lanka Standards are subject to periodical revision in order to accommodate the progress made by industry. Suggestions for improvement will be recorded and brought to the notice of the Committees to which the revisions are entrusted.

This standard does not purport to include all the necessary provisions of a contract.

© SLSI 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the SLSI.

SRI LANKA STANDARD
METHODS FOR THE DETERMINATION OF COLOUR FASTNESS OF
TEXTILE MATERIALS TO WASHING WITH SOAP OR SOAP AND SODA

NATIONAL FOREWORD

This Sri Lanka Standard was approved by the Sectoral Committee on Textiles, Clothing and Leather and was authorized for adoption and publication as a Sri Lanka Standard by the Council of the Sri Lanka Standards Institution on 2008-12-19

This Sri Lanka Standard is identical with ISO 105 – C 10:2006 Textiles – Tests for colour fastness – Part C 10 Colour fastness to washing with soap or soap and soda.

This standard supersedes SLS 52 :1998, SLS 53:1998, SLS 54:1998, SLS 55:1998 and SLS 56:1998 which are adoptions of ISO 105- C01 :1989, ISO 105- C02 :1989, ISO 105- C03 :1989, ISO 105- C04 :1989 and ISO 105- C05 :1989 respectively. These standards have been canceled and replaced by ISO 105 C – 10 :2006.

TERMINOLOGY AND CONVENTIONS

The text of the International Standard has been accepted as suitable for publication without deviation, as a Sri Lanka Standard. However certain terminology and conventions are not identical with those used in Sri Lanka Standards, attention is therefore drawn to the following :

- a) Wherever the words “International Standard/Publication” appear referring to this standard they should be interpreted as “ Sri Lanka Standard ”.
- b) The comma has been used throughout as a decimal marker. In Sri Lanka Standards it is the current practice to use a full point on the baseline as the decimal marker.
- c) Wherever page numbers are quoted, they are ISO page numbers.

CROSS REFERENCES

International Standard

Corresponding Sri Lanka Standard

ISO 105-A01 Textiles-Tests for colour fastness-
Part A01: General principles of testing.

No equivalent Sri Lanka Standard.

ISO 105-A02 Textiles-Tests for colour fastness-
Part A02: Grey scale for assessing change in colour.

No equivalent Sri Lanka Standard.

ISO 105-A03 Textiles-Tests for colour fastness-
Part A03: Grey scale for assessing staining.

No equivalent Sri Lanka Standard.

ISO 105-A04 Textiles-Tests for colour fastness-
Part A04: Method for the instrumental assessment of the degree of staining of adjacent fabrics.

No equivalent Sri Lanka Standard.

ISO 105-A05 Textiles-Tests for colour fastness-
Part A05: instrumental assessment of change in colour for determination of gray scale rating.

No equivalent Sri Lanka Standard.

ISO 105-F : Textiles-Tests for colour fastness-
Part F: Standard adjacent fabrics

No equivalent Sri Lanka Standard.

ISO 105-F01 : Textiles-Tests for colour fastness-
Part F01: Specification for wool adjacent fabric

No equivalent Sri Lanka Standard.

ISO 105-F02 : Textiles-Tests for colour fastness-
Part F02: Specification for cotton and viscose adjacent fabrics

No equivalent Sri Lanka Standard.

No equivalent Sri Lanka Standard.

ISO 105-F03 : Textiles-Tests for colour fastness-

Part F03: Specification for polyamide adjacent fabric

No equivalent Sri Lanka Standard.

ISO 105-F04 : Textiles-Tests for colour fastness-

Part F04: Specification for polyester adjacent fabric

No equivalent Sri Lanka Standard.

ISO 105-F05 : Textiles-Tests for colour fastness-

Part F05: Specification for acrylic adjacent fabric

No equivalent Sri Lanka Standard.

ISO 105-F06 : Textiles-Tests for colour fastness-

Part F06: Specification for silk adjacent fabric

No equivalent Sri Lanka Standard.

ISO 105-F-07 : Textiles-Tests for colour fastness-

Part F07: Specification for secondary acetate adjacent fabric

No equivalent Sri Lanka Standard.

ISO 105-F10 : Textiles-Tests for colour fastness-

Part F10: Specification for adjacent fabric: Multifibre

No equivalent Sri Lanka Standard.

ISO 105-J01 : Textiles-Tests for colour fastness-

Part J01: General principles for measurement of surface colour

No equivalent Sri Lanka Standard.

ISO 105-J03 : Textiles-Tests for colour fastness-

Part J03: Calculation of colour differences

No equivalent Sri Lanka Standard.

ISO 3696 Water for analytical laboratory use – Specification and test methods

Textiles — Tests for colour fastness —
Part C10:
Colour fastness to washing with soap
or soap and soda

Textiles — Essais de solidité des teintures —

Partie C10: Solidité des teintures au lavage au savon ou au savon et à la soude



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 105-C10 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

ISO 105 was previously published in thirteen “parts”, each designated by a letter (e.g. “Part A”), with publication dates between 1978 and 1985. Each part contained a series of “sections”, each designated by the respective part letter and by a two-digit serial number (e.g. “Section A02”). These sections are now being republished as separate documents, themselves designated “parts”, but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.

This first edition of ISO 105-C10 cancels and replaces ISO 105-C01:1989, ISO 105-C02:1989, ISO 105-C03:1989, ISO 105-C04:1989 and ISO 105-C05:1989, which have been technically revised.

Introduction

The test methods in this part of ISO 105 are intended to reflect the effect of washing using soap or soap and soda by domestic and commercial laundering procedures on the colour of textiles. The washes are carried out in a similar manner to the ISO 105-C08 tests, but using soap.

The general principles of testing, described in ISO 105-A01, should be understood before using this part of ISO 105.

Textiles — Tests for colour fastness —

Part C10:

Colour fastness to washing with soap or soap and soda

1 Scope

This part of ISO 105 specifies five methods intended for determining the resistance of the colour of textiles of all kinds and in all forms to washing procedures, from mild to severe, used for normal household articles.

This part of ISO 105 is designed to determine the effect of washing only on the colour fastness of the textile. It is not intended to reflect the result of the comprehensive laundering procedure.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A03, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*

ISO 105-A04, *Textiles — Tests for colour fastness — Part A04: Method for the instrumental assessment of the degree of staining of adjacent fabrics*

ISO 105-A05, *Textiles — Tests for colour fastness — Part A05: Instrumental assessment of change in colour for determination of grey scale rating*

ISO 105-F, *Textiles — Tests for colour fastness — Part F: Standard adjacent fabrics*

ISO 105-F01, *Textiles — Tests for colour fastness — Part F01: Specification for wool adjacent fabric*

ISO 105-F02, *Textiles — Tests for colour fastness — Part F02: Specification for cotton and viscose adjacent fabrics*

ISO 105-F03, *Textiles — Tests for colour fastness — Part F03: Specification for polyamide adjacent fabric*

ISO 105-F04, *Textiles — Tests for colour fastness — Part F04: Specification for polyester adjacent fabric*

ISO 105-F05, *Textiles — Tests for colour fastness — Part F05: Specification for acrylic adjacent fabric*

ISO 105-F06, *Textiles — Tests for colour fastness — Part F06: Specification for silk adjacent fabric*

ISO 105-F07, *Textiles — Tests for colour fastness — Part F07: Specification for secondary acetate adjacent fabric*

ISO 105-F10, *Textiles — Tests for colour fastness — Part F10: Specification for adjacent fabric: Multifibre*

ISO 105-J01 *Textiles — Tests for colour fastness — Part J01: General principles for measurement of surface colour*

ISO 105-J03, *Textiles — Tests for colour fastness — Part J03: Calculation of colour differences*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Principle

A specimen of the textile in contact with one or two specified adjacent fabrics is mechanically agitated under specified conditions of time and temperature in a soap, or soap and soda solution, then rinsed and dried. The change in colour of the specimen and the staining of the adjacent fabric, or fabrics, are assessed with reference to the original fabric, either with the grey scales or instrumentally.

4 Apparatus

4.1 Suitable mechanical laundering device, consisting of water bath containing a rotatable shaft which supports, radially, stainless steel containers [(75 mm ± 5 mm diameter) × (125 mm ± 10 mm high)] of capacity (550 ± 50) ml, the bottom of the containers being (45 ± 10) mm from the centre of the shaft.

The shaft/container assembly is rotated at a frequency of (40 ± 2) r/min. The temperature of the water bath is thermostatically controlled to maintain the test solution at the prescribed temperature ± 2 °C.

Other mechanically devices may be used for this test, provided that the results are identical with those obtained by the apparatus described in 4.1. Be aware of possible contamination (see the note in 7.2).

4.2 Balance, accurate to ± 0,01 g (see ISO 105-A01).

4.3 Mechanical stirrer, minimum 16,667 s⁻¹ (1 000 r/min) to ensure thorough dispersion and prevent settling.

4.4 Non-corrodible (stainless) steel balls, approximately 6 mm in diameter.

4.5 Means of heating the soap solution, such as a hot plate.

5 Reagents and materials

5.1 Soap, containing not more than 5 % moisture and complying with the following requirements based upon dry mass:

- free alkali, calculated as Na₂CO₃: 0,3 % maximum;
- free alkali, calculated as NaOH: 0,1 % maximum;
- total fatty matter: 850 g/kg minimum;
- titre of mixed fatty acids, prepared from soap: 30 °C maximum;
- Iodine value: 50 maximum.

The soap shall be free from fluorescent brightening agents.

5.2 Sodium carbonate, anhydrous (Na₂CO₃).

5.3 Soap solution, containing 5 g of soap (5.1) per litre of water (5.4) for test conditions A and B and 5 g of soap (5.1) and 2 g of sodium carbonate (5.2) per litre of water (5.4), for test conditions C, D and E.

It is recommended to vigorously disperse the soap using a mixer (4.3) in grade 3 water at (25 ± 5) °C and stir for (10 ± 1) min.

5.4 Grade 3 water, complying with ISO 3696.

5.5 Adjacent fabrics (see ISO 105-A01), either 5.5.1 or 5.5.2

5.5.1 Multifibre adjacent fabric, complying with ISO 105-F10, according to the temperature used:

— Type DW multifibre adjacent fabric containing wool and acetate (for tests at 40 °C and 50 °C and, in certain cases, to be indicated in the test report, at 60 °C);

— Type TV multifibre adjacent fabric not containing wool and acetate (in certain tests at 60 °C and in all tests at 95 °C).

5.5.2 Two single-fibre adjacent fabrics, complying with the relevant clauses of ISO 105-F01 to ISO 105-F07.

One of the adjacent fabrics shall be made of the same kind of the fibre as that of the textile to be tested or that predominating in the case of blends. The second piece shall be made of the fibre as indicated in Table 1 or, in the case of blends, of the kind of fibre second in order of predominance or as otherwise specified.

Table 1 — Pairs of adjacent fabrics

If first piece is	Second piece	
	For test at 40 °C and 50 °C	For test at 60 °C and 95 °C
Cotton	Wool	Viscose
Wool	Cotton	—
Silk	Cotton	—
Viscose	Wool	Cotton
Acetate	Viscose	Viscose
Polyamide	Wool or cotton	Cotton
Polyester	Wool or cotton	Cotton
Acrylic	Wool or cotton	Cotton

5.6 Non-dyeable fabric, if required (e.g. polypropylene).

5.7 Grey scales, for assessing change in colour and staining (ISO 105-A02; ISO 105-A03), or a **spectrophotometer** for assessing change in colour and staining complying with ISO 105-J01, ISO 105-A04 and ISO 105-A05.

6 Test specimen

6.1 If the textile to be tested is fabric, either

- a) attach a specimen 100 mm × 40 mm to a piece of the multifibre adjacent fabric (5.5.1), also 100 mm × 40 mm, by sewing along one of the shorter edges, with the multifibre adjacent fabric next to the face side of the specimen, or
- b) attach a specimen 100 mm × 40 mm between the two single-fibre adjacent fabric (5.5.2), also 100 mm × 40 mm by sewing along one of the shorter edges.

6.2 Yarn may be knitted into fabric and tested in this form. Where yarns or loose fibres are to be tested, take a mass of the yarn or loose fibres approximately equal to one-half of the combined mass of the adjacent fabrics and either

- a) place it between a 100 mm × 40 mm piece of the multifibre fabric (5.5.1) and a piece of the non-dyeable fabric (5.6) and sew them along all four sides (see ISO 105-A01), or
- b) place it between a 100 mm × 40 mm pieces of the two specified single-fibre fabrics (5.5.2) and sew them along all four sides.

6.3 Determine the mass, in grams, of the composite specimen using the balance (4.2) to aid accurate liquor ratio volumes.

7 Test procedures

7.1 Prepare the soap solution (5.3) according to the test used.

7.2 Place the composite specimen in the container together with the specified number of steel balls (Table 2). Add the necessary amount of soap solution (5.3) preheated to the test temperature ± 2 °C, according to Table 2, to give a liquor ratio of 50:1 ml/g. Close the container and operate the machine at the temperature and for the time specified in Table 2. Begin timing as soon as the container is closed.

Table 2 — Test conditions

Test number	Temperature °C	Time	Number of steel balls	Sodium carbonate
A (1)	40	30 min	0	–
B (2)	50	45 min	0	–
C (3)	60	30 min	0	+
D (4)	95	30 min	10	+
E (5)	95	4 h	10	+

Care should be taken to differentiate clearly between containers used for testing with and without fluorescent brighteners.

NOTE Containers (see 4.1) could be contaminated by the fluorescent brightening agents present in other test detergents and in commercial detergents. This could affect the colour fastness ratings of test specimens if such contaminated containers were subsequently used for tests using a detergent without fluorescent brighteners.

7.3 For all tests, remove the composite specimen at the end of the wash and place it in a 4 l beaker half filled with grade 3 water (5.4) at ambient temperature. Gently agitate, rinse for 1 min and then place the beaker under a cold running tap for 1 min.

7.4 For all methods, extract the excess water from the composite specimen by squeezing the test specimen by hand.

Open out the composite specimen by cutting the stitching except on one of the shorter sides if necessary.

7.5 Dry the specimen by pressing it flat between new filter papers to remove excess water. Then dry by hanging it in air at a temperature not exceeding 60 °C, with the parts in contact only at the line of stitching.

7.6 Assess the change in colour of the specimen and the staining of the adjacent fabric with reference to the original specimen using either the grey scales or instrumentally. See ISO 105-A02; ISO 105-A03; ISO 105-A04; ISO 105-A05; ISO 105-J03.

8 Test report

The test report shall include the following information:

- a) a reference to this part of ISO 105 (ISO 105-C10:2006);
- b) all details necessary for complete identification of the sample tested;
- c) the test conditions/test number used from Table 2;
- d) the numerical grey scale rating and/or instrumental assessment for the change in colour of the specimen;
- e) if single-fibre adjacent fabrics were used, the numerical rating for staining of each kind of adjacent fabric used;
- f) if a multifibre adjacent fabric was used, the staining of each type of fibre in the multifibre adjacent fabric, and the type of multifibre adjacent fabric used;
- g) any deviation, by agreement or otherwise, from the procedure specified.

Bibliography

- [1] ISO 105-C08, *Textiles — Tests for colour fastness — Part C08: Colour fastness to domestic and commercial laundering using a non-phosphate reference detergent incorporating a low temperature bleach activator*

SLS CERTIFICATION MARK

The Sri Lanka Standards Institution is the owner of the registered certification mark shown below. Beneath the mark, the number of the Sri Lanka Standard relevant to the product is indicated. This mark may be used only by those who have obtained permits under the SLS certification marks scheme. The presence of this mark on or in relation to a product conveys the assurance that they have been produced to comply with the requirements of the relevant Sri Lanka Standard under a well designed system of quality control inspection and testing operated by the manufacturer and supervised by the SLSI which includes surveillance inspection of the factory, testing of both factory and market samples.

Further particulars of the terms and conditions of the permit may be obtained from the Sri Lanka Standards Institution, 17, Victoria Place, Elvitigala Mawatha, Colombo 08.



SRI LANKA STANDARDS INSTITUTION

The Sri Lanka Standards Institution (SLSI) is the National Standards Organization of Sri Lanka established under the Sri Lanka Standards Institution Act No. 6 of 1984 which repealed and replaced the Bureau of Ceylon Standards Act No. 38 of 1964. The Institution functions under the Ministry of Science & Technology.

The principal objects of the Institution as set out in the Act are to prepare standards and promote their adoption, to provide facilities for examination and testing of products, to operate a Certification Marks Scheme, to certify the quality of products meant for local consumption or exports and to promote standardization and quality control by educational, consultancy and research activity.

The Institution is financed by Government grants, and by the income from the sale of its publications and other services offered for Industry and Business Sector. Financial and administrative control is vested in a Council appointed in accordance with the provisions of the Act.

The development and formulation of National Standards is carried out by Technical Experts and representatives of other interest groups, assisted by the permanent officers of the Institution. These Technical Committees are appointed under the purview of the Sectoral Committees which in turn are appointed by the Council. The Sectoral Committees give the final Technical approval for the Draft National Standards prior to the approval by the Council of the SLSI.

All members of the Technical and Sectoral Committees render their services in an honorary capacity. In this process the Institution endeavours to ensure adequate representation of all view points.

In the International field the Institution represents Sri Lanka in the International Organization for Standardization (ISO), and participates in such fields of standardization as are of special interest to Sri Lanka.