

**SRI LANKA STANDARD 484: PART 2: SECTION 2: 2019**  
**(ISO 247-2: 2018)**  
**UDC 678.03**

**METHODS OF TEST FOR  
RAW NATURAL RUBBER  
PART 2: DETERMINATION OF ASH  
SECTION 2: THERMOGRAVIMETRIC ANALYSIS  
(TGA)**

**SRI LANKA STANDARDS INSTITUTION**



**Sri Lanka Standard**  
**METHODS OF TEST FOR RAW NATURAL RUBBER**  
**PART 2: DETERMINATION OF ASH**  
**SECTION 2: THERMOGRAVIMETRIC ANALYSIS (TGA)**

**SLS 484: PART 2: SECTION 2: 2019**  
**(ISO 247-2: 2018)**

**Gr. D**

*Copyright Reserved*  
**SRI LANKA STANDARDS INSTITUTION**  
**17, Victoria Place**  
**Elvitigala Mawatha**  
**Colombo - 08**  
**Sri Lanka.**

Sri Lanka Standards are subject to periodical revision in order to accommodate the progress made by industry. Suggestions for improvement will be recorded and brought to the notice of the Committees to which the revisions are entrusted.

This Standard does not purport to include all the necessary provisions of a contract

© ISO 2018 - All right reserved.

© SLSI 2019

All right reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the SLSI.

**Sri Lanka Standard**  
**METHODS OF TEST FOR RAW NATURAL RUBBER**  
**PART 2: DETERMINATION OF ASH**  
**SECTION 2: THERMOGRAVIMETRIC ANALYSIS (TGA)**

**NATIONAL FOREWORD**

This Standard was approved by the Sectoral Committee on Chemical and Polymer Technology and authorized for adoption and publication as a Sri Lanka Standard by the Council of the Sri Lanka Standards Institution on 2019-10-22.

This Sri Lanka Standard is identical with **ISO 247-2: 2018** Rubber - Determination of ash - Part 2: Thermogravimetric analysis (TGA), published by the International Organization for Standardization (ISO).

**ISO 247-2: 2018** specifies two methods for the determination of ash from raw rubbers, compounded rubbers and vulcanizates using a thermogravimetric analyser (TGA). This International Standard has been accepted for adoption as a Sri Lanka Standard.

**TERMINOLOGY AND CONVENTIONS**

The text of the International Standard has been accepted as suitable for publication, without deviation, as a Sri Lanka Standard. However, certain terminology and conventions are not identical with those used in Sri Lanka Standards. Attention is therefore drawn to the following:

- a) Wherever the words “International Standard” appear referring to a particular Standard they should be interpreted as “Sri Lanka Standard”.
- b) The comma has been used throughout as a decimal marker. In Sri Lanka Standards it is the current practice to use the full point at the base as the decimal marker.
- c) Wherever page numbers are quoted, they are ISO page numbers.

**Cross References**

**International Standard**

ISO 248-1, Rubber, raw - Determination of volatile-matter content - Part 1: Hot-mill method and oven method

ISO 1795, Rubber, raw natural and raw synthetic - Sampling and further preparative procedures

**Corresponding Sri Lanka Standard**

SLS 484 Part 4, Methods of test for raw natural rubber - Determination of volatile matter content

SLS 1297 Method of sampling and further preparative procedures for rubber, raw natural and raw synthetic

.....

---

---

**Rubber — Determination of ash —**  
**Part 2:**  
**Thermogravimetric analysis (TGA)**

*Caoutchouc — Détermination du taux de cendres —*  
*Partie 2: Analyse thermogravimétrique (TGA)*





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland



# Contents

	Page
Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms and definitions .....</b>	<b>1</b>
<b>4 Principle .....</b>	<b>2</b>
<b>5 Reagents .....</b>	<b>2</b>
<b>6 Apparatus .....</b>	<b>2</b>
<b>7 Preparation of the test sample .....</b>	<b>2</b>
<b>8 Calibration .....</b>	<b>2</b>
<b>9 Procedure .....</b>	<b>3</b>
9.1 Method A .....	3
9.2 Method B .....	3
<b>10 Expression of results .....</b>	<b>3</b>
<b>11 Precision .....</b>	<b>4</b>
<b>12 Test report .....</b>	<b>4</b>
<b>Annex A (informative) Precision .....</b>	<b>5</b>
<b>Bibliography .....</b>	<b>7</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

A list of all parts in the ISO 247 series can be found on the ISO website.

# Rubber — Determination of ash —

## Part 2:

# Thermogravimetric analysis (TGA)

**WARNING 1** — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any other restrictions.

**WARNING 2** — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

## 1 Scope

This document specifies two methods for the determination of ash from raw rubbers, compounded rubbers and vulcanizates using a thermogravimetric analyser (TGA).

The methods are applicable to raw, compounded or vulcanized rubbers of the M, O, R and U families described in ISO 1629:

- Method A is applicable for the determination of the ash from raw rubbers.
- Method B is applicable for the determination of the ash from compounded or vulcanized rubbers.

The methods are not applicable for the determination of the ash from raw rubbers, compounded or vulcanized rubbers containing chlorine, bromine or iodine.

This document does not cover the interpretation of the ash results from the inorganic chemical contents of compounded or vulcanized rubbers.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 248-1, *Rubber, raw — Determination of volatile-matter content — Part 1: Hot-mill method and oven method*

ISO 1795, *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

## 4 Principle

A weighed test portion is heated in an atmosphere of nitrogen. After complete decomposition of the polymer, the atmosphere is switched from nitrogen to oxygen or air and the test portion is further heated until all the carbonaceous matter has been burnt off and a constant mass is reached. The mass of the residue represents the ash.

## 5 Reagents

5.1 **Dry nitrogen**, purity  $\geq 99,99\%$ .

5.2 **Dry oxygen**, purity  $\geq 99,99\%$ , or **air**.

## 6 Apparatus

6.1 **Thermogravimetric analyser**, comprising the following elements:

- a) Thermo-balance;
- b) Heating furnace;
- c) Temperature programmer;
- d) Gas flow controller, for controlling the purge gas to the balance and furnace, and keeping a constant flow rate.

6.2 **Sample pan**, platinum pan or alumina ceramic pan.

6.3 **Analytical balance**, capable of weighing to the nearest 0,1 mg.

## 7 Preparation of the test sample

7.1 For raw natural rubber, test samples shall be cut from the homogenized piece prepared in accordance with ISO 1795. For raw synthetic rubber, test samples shall be cut from the dried rubber obtained after carrying out the determination of volatile-matter content in accordance with the hot-mill method of ISO 248-1.

Take a test portion of about 2 g to 5 g from the homogenized sample and cut into pieces by hand.

7.2 Test samples of rubber compounds shall be sheeted on a mill and cut into pieces by hand.

7.3 Test samples of vulcanizates shall be sheeted or crumbed on a mill or comminuted by hand.

7.4 Care shall be taken to ensure that test samples of rubber compounds and vulcanizates are representative of the sample.

## 8 Calibration

Calibrate the thermogravimetric analyser (see [6.1](#)) according to the manufacturer's instructions.

Temperature and mass calibration should be performed.

To ensure consistent results, the thermogravimetric analyser shall be calibrated periodically. It is recommended to perform mass calibration once a month.

## 9 Procedure

### 9.1 Method A

9.1.1 Switch on and stabilize the instrument, set the temperature of furnace to 30 °C.

9.1.2 Place an empty sample pan on the platform and tare the sample pan.

9.1.3 Take about 10 mg to 20 mg from the test portion of raw rubber (see 7.1) and weigh to the nearest 0,1 mg. Place it in the sample pan. Position the sample pan on the sample platform and load the sample pan onto the thermo-balance.

9.1.4 Set the flow rate according to the manufacturer's instructions. Raise the temperature to 500 °C at a rate of 20 °C/min or 30 °C/min under an atmosphere of nitrogen. Maintain at this temperature for 1 min.

9.1.5 Switch from the stream of nitrogen to a stream of oxygen or air. Raise the temperature to 550 °C. Maintain the temperature at 550 °C for 5 min or until the mass is constant.

9.1.6 Calculate the ash using the apparatus micro-processor.

### 9.2 Method B

9.2.1 Switch on and stabilize the instrument, set the temperature of furnace to 30 °C.

9.2.2 Place an empty sample pan on the platform and tare the sample pan.

9.2.3 Take a test portion of about 10 mg to 20 mg from the test sample of compounded or vulcanized rubbers (see 7.2 or 7.3) and weigh to the nearest 0,1 mg. Place it in the sample pan. Position the sample pan on the sample platform and load the sample pan onto the thermo-balance.

9.2.4 Set the flow rate according to the manufacturer's instructions. Raise the temperature to 550 °C at a rate of 20 °C/min or 30 °C/min under an atmosphere of nitrogen. Maintain at this temperature for 1 min.

9.2.5 Switch from the stream of nitrogen to a stream of oxygen or air. Raise the temperature to 650 °C. Maintain the temperature at 650 °C for 5 min or until the mass is constant.

For compounded or vulcanized rubbers containing inorganic fillers such as calcium carbonate, a temperature of 850 °C should be used.

9.2.6 Calculate the ash using the apparatus micro-processor.

## 10 Expression of results

The ash content,  $w$ , is given, as a percentage mass fraction, by [Formula \(1\)](#):

$$w = \frac{m_1}{m_0} \times 100 \quad (1)$$

where

$m_0$  is the mass of the test portion, in milligrams;

$m_1$  is the mass of the ash, in milligrams.

## 11 Precision

See [Annex A](#).

## 12 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 247-2:2018;
- b) all details necessary for identification of the sample tested;
- c) the method employed — method A or method B;
- d) the heating rate and the final temperature reached;
- e) the type of apparatus used;
- f) the result of the test;
- g) details of any procedures not specified in this document as well as details of any incidents which could have influenced the results;
- h) the date of the test.

## Annex A (informative)

### Precision

#### A.1 General

An interlaboratory test programme (ITP) to determine the precision of the two test methods specified in this document was conducted using thermogravimetric analysers in April 2017. The precision evaluated was a type 1 precision in accordance with Method B in ISO 19983. Precision concepts and nomenclature are also given in ISO 19983.

Nine laboratories participated in the ITP and four different materials (Raw rubber: NR and NBR, compounded SBR, vulcanized NR) were used. A test result was taken to be the average value of two measurements. Test results were obtained on two different days at intervals of one week. Two measurements were repeated for each day.

#### A.2 Precision results

The precision results are given in [Table A.1](#) for method A and [Table A.2](#) for method B. These results were obtained using outlier deletion procedures as described in ISO 19983.

**Repeatability:** The difference between two day test (value) averages, found on nominally identical material samples under correct operation of this test method, exceed the tabulated day-to-day repeatability on average not more than once in 20 cases.

**Reproducibility:** The difference between two independently measured test (value) averages, found in two laboratories using correct operation of this test method on nominally identical material samples, exceed the tabulated reproducibility not more than once in 20 cases.

**Table A.1 — Precision data for Method A**

Material	Mean content	Within lab			Between labs			No. of labs <sup>a</sup>
		$s_{rD}$	$r_D$	$(r_D)$	$s_R$	$R$	$(R)$	
NR	0,29	0,039	0,110	37,9	0,100	0,283	97,6	8
NBR	0,55	0,067	0,190	34,5	0,096	0,272	49,5	9

The symbols used in this table are defined as follows:

$s_{rD}$  is the day-to-day repeatability standard deviation;

$r_D$  is the day-to-day repeatability, in measurement units;

$(r_D)$  is the relative day-to-day repeatability, in percent;

$s_R$  is the reproducibility standard deviation;

$R$  is the reproducibility, in measurement units;

$(R)$  is the relative reproducibility, in percent.

<sup>a</sup> The final number of laboratories in the ITP after deletion of outliers.

**Table A.2 — Precision data for Method B**

Material	Mean content	Within lab			Between labs			No. of labs <sup>a</sup>
		$s_{rD}$	$r_D$	$(r_D)$	$s_R$	$R$	$(R)$	
SBR	2,06	0,057	0,161	7,81	0,289	0,818	39,7	8
NR	5,12	0,107	0,303	5,92	0,239	0,676	13,2	7

For the meanings of the symbols used in this table, see Table A.1.

<sup>a</sup> The final number of laboratories in the ITP after deletion of outliers.



## Bibliography

- [1] ISO 1629, *Rubber and latices — Nomenclature*
- [2] ISO 19983, *Rubber — Determination of precision of test methods*



## **SLS CERTIFICATION MARK**

*The Sri Lanka Standards Institution is the owner of the registered certification mark shown below. Beneath the mark, the number of the Sri Lanka Standard relevant to the product is indicated. This mark may be used only by those who have obtained permits under the SLS certification marks scheme. The presence of this mark on or in relation to a product conveys the assurance that they have been produced to comply with the requirements of the relevant Sri Lanka Standard under a well designed system of quality control inspection and testing operated by the manufacturer and supervised by the SLSI which includes surveillance inspection of the factory, testing of both factory and market samples.*

*Further particulars of the terms and conditions of the permit may be obtained from the Sri Lanka Standards Institution, 17, Victoria Place, Elvitigala Mawatha, Colombo 08.*



## **SRI LANKA STANDARDS INSTITUTION**

The Sri Lanka Standards Institution (SLSI) is the National Standards Organization of Sri Lanka established under the Sri Lanka Standards Institution Act No. 6 of 1984 which repealed and replaced the Bureau of Ceylon Standards Act No. 38 of 1964. The Institution functions under the Ministry of Science & Technology.

The principal objects of the Institution as set out in the Act are to prepare standards and promote their adoption, to provide facilities for examination and testing of products, to operate a Certification Marks Scheme, to certify the quality of products meant for local consumption or exports and to promote standardization and quality control by educational, consultancy and research activity.

The Institution is financed by Government grants, and by the income from the sale of its publications and other services offered for Industry and Business Sector. Financial and administrative control is vested in a Council appointed in accordance with the provisions of the Act.

The development and formulation of National Standards is carried out by Technical Experts and representatives of other interest groups, assisted by the permanent officers of the Institution. These Technical Committees are appointed under the purview of the Sectoral Committees which in turn are appointed by the Council. The Sectoral Committees give the final Technical approval for the Draft National Standards prior to the approval by the Council of the SLSI.

All members of the Technical and Sectoral Committees render their services in an honorary capacity. In this process the Institution endeavours to ensure adequate representation of all view points.

In the International field the Institution represents Sri Lanka in the International Organization for Standardization (ISO), and participates in such fields of standardization as are of special interest to Sri Lanka.