

SRI LANKA STANDARD 916 : PART 1 : 1991

UDC 678.021.17 : 661.666.4

Reaffirmed

2016

SPECIFICATION FOR
RUBBER COMPOUNDING INGREDIENTS

PART 1 - CARBON BLACK - HAF N 330 TYPE

SRI LANKA STANDARDS INSTITUTION

SPECIFICATION FOR RUBBER COMPOUNDING INGREDIENTS
PART 1 : CARBON BLACK - HAF N 330 TYPE

SLS 916:1991

Gr. 4

Copyright Reserved

SRI LANKA STANDARDS INSTITUTION
53, Dharmapala Mawatha,
Colombo 3,
Sri Lanka.

CONSTITUTION OF THE DRAFTING COMMITTEE
on Rubber Compounding Ingredients

CHAIRMAN

Mr I.A. Wickramaratna

REPRESENTING

Sri Lanka Tyre Corporation

MEMBERS

Mrs Indira Fernando

Associated Motorways Limited

Dr P.Y. Gunapala

Ceylon Institute of Scientific
and Industrial Research

Mr H. de S. Mutukumarana

Mackwoods Limited

Mr Asoka Perera

Mutiform Chemicals

Mr Ranjan Perera

Richard Pieris &
Company Limited

Mr J. Samarasinghe

Chemical Industries (Colombo)
Limited

Dr W.H.G. Seneviratne

Rubber Research Institute

Mr G.B. Shaw

Ansell Lanka Limited

Mr K.J. Wanasinghe

Industrial Development Board

TECHNICAL SECRETARIAT

SRI LANKA STANDARDS INSTITUTION

Sri Lanka Standards are subject to periodical revision in order to accommodate the progress made by industry. Suggestions for improvement will be recorded and brought to the notice of the Committees to which the revisions are entrusted.

This standard does not purport to include all the necessary provisions of a contract.

SRI LANKA STANDARD
SPECIFICATION FOR RUBBER COMPOUNDING INGREDIENTS
PART 1 : CARBON BLACK - HAF N 330 TYPE

FOREWORD

This Sri Lanka Standard was authorized for adoption and publication by the Council of the Sri Lanka Standards Institution on 1991-04-02, after the draft, finalized by the Drafting Committee on Rubber Compounding Ingredients had been approved by the Chemicals Divisional Committee.

Clause 4.1 of this specification calls for agreement between the purchaser and the supplier.

This specification covers only the HAF N 330 Type (classification based on ASTM D 1765 : 1989 - Standard classification system for Carbon Blacks used in Rubber products) which is widely used in rubber industry as an ingredient for test mixes.

For the purpose of deciding whether a particular requirement of this specification is complied, with the final value, observed or calculated, expressing the result of a test or an analysis, shall be rounded off in accordance with CS 102. The number of significant places retained in the rounded off value shall be the same as that of the specified value in this specification.

In the preparation of this specification, the assistance obtained from the publications of the International Organization for Standardization, American society for Testing and Materials and British Standards Institution is gratefully acknowledged.

1 SCOPE

This specification prescribes the requirements and methods of sampling and test for carbon black HAF N 330.

2 REFERENCES

CS 102 - Presentation of numerical values
SLS 428 - Random sampling methods
SLS 899 - Methods of Test for rubber compounding ingredients
Part 1 : Carbon black

3 REQUIREMENTS**3.1 Appearance**

The material shall be free from visible impurities.

3.2 Other requirements

The material shall conform to the requirements given in Table 1 when tested by the methods prescribed in Column 4 of the table.

Table 1 - Other requirements for carbon black - HAF N 330

Sl No. (1)	Characteristic (2)	Requirement (3)	Method of test (4)
i)	Iodine absorption number, mg/g	82 \pm 6	SLS 899 Sec. 4
ii)	DBP absorption number, ml/100 g	102 \pm 4	SLS 899 Sec. 12
iii)	Pour density, kg/m ³	375 \pm 30	SLS 899 Sec. 5
iv)	Toluene discoloration per cent by transmission, min.	85	SLS 899 SEC. 10
v)	Loss on heating at 105 °C, for one h, per cent by mass, max.	2.5	SLS 899 Sec. 2
vi)	pH value	8 to 9	6.2
vii)	Tinting strength per cent by mass	103 \pm 5	SLS 899 Sec.14
viii)	Sieve residue on 45 μ m, sieve per cent by mass, max.	0.10	SLS 899. Sec. 7

4 PACKAGING AND MARKING

4.1 Packaging

The material shall be packed in bags as agreed to between the purchaser and the supplier.

4.2 Marking

Each bag shall be marked or labelled legibly and indelibly with the following :

- a) Name of the product, carbon black - HAF N 330;
- b) Name and address of the manufacturer and/or distributor (including the country of origin);
- c) Registered trade mark, if any;
- d) Batch or code number; and
- e) Net mass, in kilograms.

NOTE

Attention is drawn to certification facilities offered by the Sri Lanka Standards Institution See the inside back cover of the specification.

5 SAMPLING

5.1 Lot

In any consignment all bags of carbon black, of the same type belonging to one batch of manufacture or supply shall constitute a lot.

5.2 Scale of sampling

5.2.1 Samples shall be tested from each lot for ascertaining its conformity to the requirements of this specification.

5.2.2 The number of bags to be selected from a lot shall be in accordance with Table 2.

TABLE 2 - Scale of sampling

Number of bags in the lot (1)	Number of bags to be selected (2)
Up to 150	3
151 to 1 500	5
1 501 to 15 000	10
15 001 and above	15

5.2.3 The bags shall be selected at random. In order to ensure randomness of selection tables of random numbers as given in SLS 428 shall be used.

5.3 Preparation of composite sample

A sufficient quantity of carbon black shall be drawn from the geometric centre of the bag selected as in 5.2 using a suitable sampling tube, or an appropriate instrument. The material thus obtained shall be mixed together and reduced to form the composite sample of required size by using coning and quartering method. The composite sample thus prepared shall be transferred into an airtight container.

5.4 Number of tests

5.4.1 Each bag selected as in 5.2 shall be inspected for packaging and marking requirements.

NOTE

This may be carried out at the place of sampling.

5.4.2 The composite sample prepared as in 5.3 shall be tested for the requirements given in 3.2.

6 METHODS OF TEST

6.1 Tests shall be carried out as prescribed in SLS 899.

6.2 Weigh 5 g of carbon black to the nearest 0.01 g, in a 100-ml glass beaker. Add 50 ml of boiling distilled water and 2 to 3 drops of acetone. Cover with a watch glass and boil the mixture for 15 minutes. Cool it to the room temperature and determine the pH value of the solution while swirling using a pH meter.

7 CRITERIA FOR CONFORMITY

A lot shall be declared as conforming to the requirements of this specification if the following conditions are satisfied:

7.1 Each bag inspected as in 5.4.1 satisfies the packaging and marking requirements.

7.2 The composite sample tested as in 5.4.2 satisfies the relevant requirements.

SRI LANKA STANDARDS INSTITUTION

The Sri Lanka Standards Institution (SLSI) is the National Standards Organization of Sri Lanka established under the Sri Lanka Standards Institution Act No. 6 of 1984 which repealed and replaced the Bureau of Ceylon Standards Act No. 38 of 1964. The Institution functions under the Ministry of Science & Technology.

The principal objects of the Institution as set out in the Act are to prepare standards and promote their adoption, to provide facilities for examination and testing of products, to operate a Certification Marks Scheme, to certify the quality of products meant for local consumption or exports and to promote standardization and quality control by educational, consultancy and research activity.

The Institution is financed by Government grants, and by the income from the sale of its publications and other services offered for Industry and Business Sector. Financial and administrative control is vested in a Council appointed in accordance with the provisions of the Act.

The development and formulation of National Standards is carried out by Technical Experts and representatives of other interest groups, assisted by the permanent officers of the Institution. These Technical Committees are appointed under the purview of the Sectoral Committees which in turn are appointed by the Council. The Sectoral Committees give the final Technical approval for the Draft National Standards prior to the approval by the Council of the SLSI.

All members of the Technical and Sectoral Committees render their services in an honorary capacity. In this process the Institution endeavours to ensure adequate representation of all view points.

In the International field the Institution represents Sri Lanka in the International Organization for Standardization (ISO), and participates in such fields of standardization as are of special interest to Sri Lanka.

SLS CERTIFICATION MARK

The Sri Lanka Standards Institution is the owner of the registered certification mark shown below. Beneath the mark, the number of the Sri Lanka Standard relevant to the product is indicated. This mark may be used only by those who have obtained permits under the SLS certification marks scheme. The presence of this mark on or in relation to a product conveys the assurance that they have been produced to comply with the requirements of the relevant Sri Lanka Standard under a well designed system of quality control inspection and testing operated by the manufacturer and supervised by the SLSI which includes surveillance inspection of the factory, testing of both factory and market samples.

Further particulars of the terms and conditions of the permit may be obtained from the Sri Lanka Standards Institution, 17, Victoria Place, Elvitigala Mawatha, Colombo 08.

