

SRI LANKA STANDARD 137 : PART 3 : 1981

UDC 677.21.061.1 : 687.31

**SPECIFICATION FOR
GREY COTTON YARN
PART 3—HOSIERY
(FIRST REVISION)**

BUREAU OF CEYLON STANDARDS

SPECIFICATION FOR GREY COTTON YARNS

PART 3 : HOSIERY (FIRST REVISION)

SLS 137:Part 3:1981

Gr.6

Copyright Reserved

BUREAU OF CEYLON STANDARDS

53, Dharmapala Mawatha,

Colombo 3,

Sri Lanka.

SRI LANKA STANDARD
SPECIFICATION FOR GREY COTTON YARNS
PART 3 : HOSIERY
(FIRST REVISION)

FOREWORD

This Sri Lanka Standard Specification was prepared by the Drafting Committee on Grey Cotton Yarns. It was approved by the Textiles Divisional Committee of the Bureau of Ceylon Standards and was authorized for adoption and publication by the Council of the Bureau on 1981-01-29.

This standard is based on CS 137 which is withdrawn on the date of publication of this standard.

CS 137 covered requirements of grey cotton yarn intended for use in handloom, powerloom and hosiery industries. In the present revision it is intended to give requirements in separate standards in order to have more comprehensive standards to suit the needs of each industry. Revised standards for powerloom and handloom yarn have already been prepared and are available as SLS 137:Part 1 and Part 2.

This standard gives requirements for grey cotton yarn intended for use by the hosiery industry. The yarn strength index values have been revised and maximum linear irregularity values are specified.

All standard values given in this specification are in SI units. However, English cotton count equivalents for linear density in tex values are given in an appendix for guidance.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or observation shall be rounded off in accordance with CS 102. The number of figures to be retained in the rounded off value shall be the same as that of the specified value in this standard.

In the preparation of this standard assistance derived from publications of the Indian Standards Institution, American Society for Testing and Materials and Zellweger Uster Ltd. is gratefully acknowledged.

1 SCOPE

This specification covers the requirements of grey cotton yarns intended for use in hosiery.

2 REFERENCES

This standard makes reference to the following standards.

- CS 19 Designation of the structure of yarn
- SLS 20 Method for determination of the size of yarns (First Revision)
- SLS 23 Twist in yarns - Direct counting method (First Revision)
- CS 102 Presentation of numerical values
- SLS 428 Random sampling method

3 DEFINITIONS

For the purpose of this standard, the following definitions shall apply :

- 3.1 **nep (cotton yarn)** : A defect in a yarn characterized by a small knot of entangled fibres.
- 3.2 **skein** : A continuous length of yarn measuring 100 m in the form of a coil made on a 1 m girth reel.
- 3.3 **skein breaking load** : The breaking load of a skein determined by testing on a pendulum type testing machine the rate of traverse being 300 ± 15 mm/min.
- 3.4 **slub (bunch, slug)** : A defect in a yarn characterized by a segment not over 6 mm in length that shows an abrupt increase in diameter caused by more fibres matted in this particular place.
- 3.5 **snarl** : A short length of yarn which has twisted on itself due to lively twist.
- 3.6 **tex** : The mass in grams of 1 kilometre of yarn.
- 3.7 **thick place** : A defect in a yarn, extending for 6 mm or more characterized by a diameter greater than that of the adjoining segments; the unevenness is normally caused by a greater number of fibres per yarn cross-section than usual.
- 3.8 **thin place** : A defect in a yarn characterized by a segment that is substantially (at least 25 per cent) smaller in diameter than the average diameter of the yarn. A thin place may be of any length.

3.9 unevenness U per cent : The mean deviation in mass/unit length of 8 mm increments of yarn determined by an electronic type unevenness tester.

3.10 yarn appearance : Visual effect obtained by viewing samples wound with a designated traverse on a black board of designated size.

3.11 yarn strength index (YSI) : The numerical value of the breaking load, in newtons of a 100 m skein divided by the linear density in tex multiplied by the value of the standard gravity g .

4 GENERAL REQUIREMENTS

4.1 The yarn shall be reasonably free from leaf particles, foreign matter, neps, snarls, slubs, bad knots, knots with long tails and stains. There shall be no loose ends in the yarn package. Yarn in cones shall be free from common defects listed in Appendix A.

5 SPECIFIC REQUIREMENTS

5.1 Composition

The yarn shall be 100 per cent cotton.

5.2 Appearance

In the case of single yarns the appearance of the yarn shall be graded in accordance with American Society for Testing and Materials (ASTM) grades (See ASTM D 2255 - Grading of cotton yarns for appearance). The average black board appearance shall be at least Grade C.

NOTE - ASTM grading of cotton yarns for appearance is done by comparing the sample wound on a black board with a series of standard photographic plates.

5.3 Count of yarn

The yarn of various counts shall conform to the requirements specified in Table 1.

5.3.1 A tolerance of ± 3 per cent on the average in the count of yarn shall however be permissible.

5.3.2 The coefficient of variation shall not exceed 5 per cent.

5.3.3 The count of yarn shall be determined by the method described in SLS 20.

5.4 Yarn strength index (YSI)

5.4.1 The yarn strength index (YSI) of yarns shall be not less than the values prescribed in Table 1.

5.4.2 Yarn strength index (YSI) shall be calculated by the following formula :

$$\text{Yarn strength index} = \frac{L}{gt} \times 1000$$

where

L = Skein breaking load in newtons ;

t = Universal count of yarn in tex ; and

g = Numerical value of the standard gravity = 9.8066

TABLE 1 - Particulars of grey cotton yarn for hosiery
(See 5.3, 5.4, 5.6 and Appendix B)

No.	Count of yarn in tex	Carded or Combed	Minimum YSI	Maximum Twist/m
1	30	Carded	1300	670
2	25	Carded	1400	730
3	20	Carded	1450	820
4	17	Carded	1500	900
5	15	Carded	1500	950
6	20	Combed	1500	820
7	15	Combed	1550	950
8	12	Combed	1600	1060
9	10	Combed	1650	1160

5.5 Final twist

5.5.1 The final twist of yarn shall be Z twist.

5.5.2 The final twist of yarn shall be determined by the method described in CS 19.

5.6 Twist per metre

5.6.1 Twist per metre of yarns shall not be more than the values prescribed in Table 1.

5.6.2 The twist per metre of yarns shall be determined by the method described in SLS 23.

5.7 Unevenness

5.7.1 For counts finer than 12 tex the maximum mean linear irregularity (U per cent) of cotton yarn shall be not more than the value prescribed in Table 2.

NOTE - $C.V. = 1.25 \times U$ per cent

Where U per cent is the percentage of mean deviation of unevenness and C.V. is the percentage of coefficient of variation of unevenness.

TABLE 2 - Mean linear irregularity of cotton yarn (hosiery)

No.	Count of yarn in tex	Carded or Combed	Maximum mean linear irregularity (U%)
1	30	Carded	14.3
2	25	Carded	14.7
3	20	Carded	15.3
4	17	Carded	15.5
5	15	Carded	16.0
6	20	Combed	12.2
7	15	Combed	12.7
8	12	Combed	13.2
9	10	Combed	13.7

6 PACKAGING

6.1 Packaging of cones

All yarn for sale in cones shall be individually wrapped in polythene film or similar material to avoid damage and these shall be packed in cartons. An insert to prevent collapsing shall be incorporated at the base of each cone. Unless otherwise agreed on between the buyer and the seller, the net mass of a cone shall be 1.25 kg and these shall be packed in cartons having 36 cones per carton.

7 LABELLING AND MARKING

7.1 Labelling of cones

Each cone shall be labelled with the following information :

- a) Count of yarn in tex ; and
- b) Name of the manufacturer.

7.2 Labelling of cartons

Each carton shall be labelled with the following information :

- a) Count of yarn in tex ;
- b) Name of the manufacturer ;
- c) Number of cones in carton ;
- d) Gross mass in kilograms ; and
- e) Net mass in kilograms.

NOTE - Net mass is oven dried mass x 8.5 per cent moisture regain.

8 SAMPLING

8.1 Scale of sampling

8.1.1 Lot

All the bales or cases of cotton yarn of the same count manufactured at one time and relatively uniform conditions of production, delivered to one buyer against one despatch note shall constitute a lot.

8.1.2 Samples shall be tested from each lot for ascertaining the conformity of the yarn to the requirements of this specification.

8.1.3 The number of bales or cases to be selected from a lot shall depend on the size of the lot, and shall be in accordance with Table 3.

TABLE 3 - No. of bales or cases to be selected

Lot size	No. of bales or cases to be selected
Up to 8	3
9 to 15	4
16 to 25	5
26 to 50	7
51 to 100	8
101 to 150	9
151 to 300	10
301 and above	12

8.1.4 From each bale or case selected as above five bundles or packages shall be selected.

8.1.5 Bales or cases and bundles or packages shall be drawn at random. To ensure randomness of selection random number tables as given in SLS 428 shall be used.

8.2 Test specimen

From each bundle or package selected as above one test specimen shall be selected (discarding at least first 50 m from the package) to represent the bundle or package.

8.3 Number of tests and length of the test specimen

8.3.1 Tests for each of the requirements given in 5 shall be conducted on each of the test specimens.

8.3.2 The length of the test specimen to test for requirements given in 5.1, 5.2, 5.3, 5.4 and 5.5 shall be in accordance with Table 4.

TABLE 4 - Length of test specimen

Count	Length in metres
5 tex and above	100
below 5 tex	200

8.3.3 The length required for the test prescribed in 5.6 shall be in accordance with the length specified in the tester.

9 CRITERIA FOR CONFORMITY

The lot shall be considered to be in conformity with the requirements of this specification if the number of test specimens selected to represent the bundles or packages not conforming to any one or more requirements of this specification, is less than or equal to the corresponding acceptance number given in Column 2 of Table 5.

TABLE 5 - Criteria for conformity

No. of test specimens tested	Acceptance no.
15	1
20	1
25	1
35	2
40	2
45	3
50	3
60	4

APPENDIX A

(4.1)

COMMON DEFECTS OF YARN ON CONES

A.1 The yarn package shall be free from the following defects:

- a) Stitches of more than 25 mm in length at the base ;
- b) Excessive stitches at the nose of cones ;
- c) Soft cones ;
- d) Collapsed cones ;
- e) Prominent stairs inclusive of chalk and other markings ;
- f) Cut threads ; and
- g) Absence of tail end where required (the length of tail end should not be less than 300 mm).

APPENDIX B

(Table 1)

Traditional English cotton count values and their rounded tex value equivalents.

No.	Traditional English cotton count	Rounded tex value
1	20 S	30
2	24 S	25
3	30 S	20
4	36 S	16.5
5	40 S	14.5
6	50 S	12
7	60 S	10

SLS CERTIFICATION MARK

The Sri Lanka Standards Institution is the owner of the registered certification mark shown below. Beneath the mark, the number of the Sri Lanka Standard relevant to the product is indicated. This mark may be used only by those who have obtained permits under the SLS certification marks scheme. The presence of this mark on or in relation to a product conveys the assurance that they have been produced to comply with the requirements of the relevant Sri Lanka Standard under a well designed system of quality control inspection and testing operated by the manufacturer and supervised by the SLSI which includes surveillance inspection of the factory, testing of both factory and market samples.

Further particulars of the terms and conditions of the permit may be obtained from the Sri Lanka Standards Institution, 17, Victoria Place, Elvitigala Mawatha, Colombo 08.



SRI LANKA STANDARDS INSTITUTION

The Sri Lanka Standards Institution (SLSI) is the National Standards Organization of Sri Lanka established under the Sri Lanka Standards Institution Act No. 6 of 1984 which repealed and replaced the Bureau of Ceylon Standards Act No. 38 of 1964. The Institution functions under the Ministry of Science & Technology.

The principal objects of the Institution as set out in the Act are to prepare standards and promote their adoption, to provide facilities for examination and testing of products, to operate a Certification Marks Scheme, to certify the quality of products meant for local consumption or exports and to promote standardization and quality control by educational, consultancy and research activity.

The Institution is financed by Government grants, and by the income from the sale of its publications and other services offered for Industry and Business Sector. Financial and administrative control is vested in a Council appointed in accordance with the provisions of the Act.

The development and formulation of National Standards is carried out by Technical Experts and representatives of other interest groups, assisted by the permanent officers of the Institution. These Technical Committees are appointed under the purview of the Sectoral Committees which in turn are appointed by the Council. The Sectoral Committees give the final Technical approval for the Draft National Standards prior to the approval by the Council of the SLSI.

All members of the Technical and Sectoral Committees render their services in an honorary capacity. In this process the Institution endeavours to ensure adequate representation of all view points.

In the International field the Institution represents Sri Lanka in the International Organization for Standardization (ISO), and participates in such fields of standardization as are of special interest to Sri Lanka.