

**SRI LANKA STANDARD 1359 : 2008**  
**ISO 16549 : 2004**

**METHOD FOR DETERMINATION OF  
UNEVENNESS OF TEXTILE STRANDS  
USING CAPACITANCE METHOD**

**SRI LANKA STANDARDS INSTITUTION**



**Sri Lanka Standard**  
**METHOD FOR DETERMINATION OF UNEVENNESS OF**  
**TEXTILE STRANDS USING CAPACITANCE METHOD**

**SLS 1359 : 2008**  
**ISO 16549 : 2004**  
**(Superseding SLS 674 : 1984)**

Gr. E

**SRI LANKA STANDARDS INSTITUTION**  
**17 Victoria Place**  
**Elvitigala Mawatha**  
**Colombo 8**  
**SRI LANKA.**

Sri Lanka Standards are subject to periodical revision in order to accommodate the progress made by industry. Suggestions for improvement will be recorded and brought to the notice of the Committees to which the revisions are entrusted.

This standard does not purport to include all the necessary provisions of a contract.

© SLSI 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the SLSI.

**Sri Lanka Standard**  
**METHOD FOR DETERMINATION OF UNEVENNESS OF TEXTILE STRANDS**  
**USING CAPACITANCE METHOD**

**NATIONAL FOREWORD**

This standard was approved by the Sectoral Committee on Textiles, Clothing and Leather and was authorized for adoption and publication as a Sri Lanka Standard by the Council of the Sri Lanka Standards Institution on 2008-12-19.

This Sri Lanka Standard is identical with ISO16549:2004 Textiles – Unevenness of textile strands – Capacitance method. This standard supercedes SLS 674:1984 Determination of short-term irregularity of linear density of textile slivers, roving and yarns using an electronic evenness tester which was an adoption of ISO 2649: 1984. ISO 2649:1984 has been cancelled and replaced by ISO 16549:2004.

**TERMINOLOGY AND CONVENTIONS**

The text of the International Standard has been accepted as suitable for publication without deviation, as a Sri Lanka Standard. However certain terminology and conventions are not identical with those used in Sri Lanka Standards, attention is therefore drawn to the following :

- a) Wherever the words “International Standard/Publication” appear referring to this standard they should be interpreted as “ Sri Lanka Standard ”.
- b) The comma has been used throughout as a decimal marker. In Sri Lanka Standards it is the current practice to use a full point on the baseline as the decimal marker.
- c) Wherever page numbers are quoted, they are ISO page numbers.

**CROSS REFERENCES**

**International Standard**

**Corresponding Sri Lanka Standard**

ISO 139 Textiles-standard atmospheres for conditioning and testing

SLS 16 Textiles – Standard atmospheres for conditioning and testing



**INTERNATIONAL  
STANDARD**

**ISO  
16549**

First edition  
2004-06-01

---

---

**Textiles — Unevenness of textile  
strands — Capacitance method**

*Textiles — Irrégularité des fils textiles — Méthode capacitive*



Reference number  
ISO 16549:2004(E)

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland



## Contents

Page

<b>1</b>	<b>Scope .....</b>	<b>1</b>
<b>2</b>	<b>Normative references .....</b>	<b>1</b>
<b>3</b>	<b>Terms and definitions .....</b>	<b>1</b>
<b>4</b>	<b>Principle .....</b>	<b>2</b>
<b>5</b>	<b>Apparatus .....</b>	<b>3</b>
<b>6</b>	<b>Atmosphere for conditioning and testing .....</b>	<b>4</b>
<b>7</b>	<b>Sampling .....</b>	<b>4</b>
<b>8</b>	<b>Procedure .....</b>	<b>5</b>
<b>9</b>	<b>Calculations and expression of results .....</b>	<b>6</b>
<b>10</b>	<b>Test report .....</b>	<b>6</b>
	<b>Annex A (informative) Other methods for the determination of unevenness .....</b>	<b>8</b>
	<b>Bibliography .....</b>	<b>10</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16549 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

This International Standard cancels and replaces ISO 2649 which is now obsolete.

## **Introduction**

In the 1960s the International Wool Textile Organization (IWTO) prepared an unevenness method destined for yarns and other strands made of wool. The method was adopted by ISO as ISO 2649:1974. It contains a discussion of the principles of unevenness testing and refers to the then-popular unevenness tester, the 1960s model of the Uster Evenness Tester, which was obsolete in mid-2000 when the present International Standard was written. Later, the IWTO prepared a new method, IWTO-18-00, published in 2000.

ISO 16549 has mostly new wording but includes some elements of ISO 2649 and of IWTO-18-00 – with thanks to IWTO.



# Textiles — Unevenness of textile strands — Capacitance method

## 1 Scope

This International Standard describes a method, using capacitance measuring equipment, for determining the unevenness of linear density along the length of textile strands.

The method is applicable to tops, slivers, rovings, spun yarns and continuous filament yarns, made from either natural or man-made fibres, in the range of 4 tex (g/km) to 80 ktex (kg/km) for staple-fibre strands and 1 tex (g/km) to 600 tex (g/km) for continuous-filament yarns. It is not applicable to fancy yarns or to strands composed fully or partly of conductive materials such as metals; the latter require an optical sensor (see A.4).

The method describes the preparation of a variance-length curve, as well as the determination of periodicities of linear density. It covers also the counting of imperfections in the yarn, namely of neps and of thick and thin places.

Irregularities in the distribution of additives such as sizes, in moisture content and in fibre blending may increase the measured unevenness above its true value.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **unevenness**

variation of linear density along the length of a continuous strand or yarn

NOTE The term is also used occasionally for the variation of yarn diameter.

### 3.2

#### **coefficient-of-variation unevenness**

$CV_u$

value of **unevenness** (3.1) expressed as a coefficient of variation

NOTE 1 The coefficient-of-variation unevenness is expressed in percent, for example  $CV_u = 18,3\%$ .

NOTE 2 See also 4.5 and 4.6.

### 3.3

#### **mean-deviation unevenness**

$U_u$

value of **unevenness** (3.1) expressed as an average mean deviation

NOTE 1 The mean-deviation unevenness is expressed in percent, for example,  $U_u = 14,6\%$ .

NOTE 2 See also 4.5 and 4.6.

**3.4**  
**capacitor length**

effective length of the capacitor in the direction of the specimen movement, usually 8 mm to 20 mm

**3.5**  
**length between**

$L_b$   
length of the test specimen for which the instrument takes an individual reading of mass

NOTE 1 The unevenness value decreases as  $L_b$  is increased.

NOTE 2 In the capacitance method,  $L_b$  is normally the capacitor length but it can be increased electronically.

NOTE 3  $L_b$  is sometimes referred to in the literature as  $B$ .

**3.6**  
**length within**

$L_w$   
length of the specimen for which an individual value of unevenness is determined and a reading is given

NOTE 1 The unevenness value increases as  $L_w$  is increased. When  $L_w$  is more than 100 m or so, then a further lengthening of  $L_w$  increases  $CV_u$  (or  $U_u$ ) only slightly.

NOTE 2  $L_w$  is sometimes referred to in the literature as  $W$ .

**3.7**  
**total measured length**

sum of all measured lengths  $L_w$

**3.8**  
**nep**  
tightly tangled knot-like mass of unorganized fibres

**3.9**  
**package**  
yarn wound to a shape, which may be supported (for example, bobbins, cones) or unsupported (for example, skeins, cakes), suitable for conditioning and testing

**3.10**  
**spectrogram**  
attachment to unevenness testers for the calculation and presentation of periodic variations in the strand

**3.11**  
**thick place**  
yarn defect with linear density substantially (at least 50 %) greater than that of the adjoining segments of the yarn and extending for at least 5 mm

**3.12**  
**thin place**  
yarn defect with linear density substantially (at least 50 %) smaller than that of the adjoining segments of the yarn and extending for at least 5 mm

## 4 Principle

**4.1** A specimen is passed between two plates of a capacitor causing changes in capacitance which are proportional to the changes of mass of the specimen. The instrument evaluates these changes and reports them as  $CV_u$  or  $U_u$ .

**4.2** The fibre dielectric constant is also a factor determining the capacitance change. As long as the dielectric constant is unchanging (non-blended strands or perfectly uniform blending), the dielectric constant has no influence on the unevenness reading, which depends solely on the variation of mass. If the dielectric constant differs for the types of fibres in a blend and if, at the same time, the blend is irregular, then the reading of unevenness is increased above its true value. The interpretation of results therefore requires caution.

**4.3** Several studies have been conducted over the years, see Reference [3] for example, comparing the true unevenness of a specimen, determined by cutting and weighing (see A.3.1), with the reading from an unevenness tester. Good agreement was obtained, so the readings from the tester can be taken as being the true unevenness value.

**4.4** The value of unevenness has meaning only if both  $L_b$  and  $L_w$  are known and they should, in principle, always be reported, preferably as  $CV_u(L_b, L_w)$ .

EXAMPLE  $CV_u(10\text{ mm}, 1\ 000\text{ m})$ .

In practice, these two values are usually left unstated and are assumed to be those of the most commonly used unevenness tester, namely

- $L_b$ : 8 mm for yarns, 12 mm for rovings, 20 mm for slivers and tops;
- $L_w$ : total length of yarn on the package.

**4.5** There are two possible expressions for unevenness,  $CV_u$  and  $U_u$ . The  $U_u$  is now obsolete and its use, while permitted, is discouraged.  $CV_u$  is the preferred expression.

**4.6** If mass is distributed near to “normal”, then the ratio of  $CV_u/U_u$  is approximately 1,25. This conversion factor must be used cautiously because, in case of departures from normality, the ratio can be considerably different. The conversion factor may be used to convert a table of quality levels from  $U_u$  to  $CV_u$ .

**4.7** When  $CV_u$  is plotted against  $L_b$ , a “variance-length curve” is obtained which gives additional information on the material's unevenness. When the plot is made on log-log paper, then the curve is almost a straight line and its slope gives information on the relationship between short-term and long-term unevenness.

**4.8** Unevenness testers usually contain a spectrogram, which analyses the data and provides information on periodic variations of linear density. This information is useful in finding faults in the processing. The analysis uses an algorithm based on the Fourier transformation.

**4.9** Unevenness testers usually contain a counter for yarn imperfections, namely neps, and thick and thin places. The level beyond which the imperfections are counted can be adjusted.

**4.10** Unevenness is a fundamental feature of yarn construction. It influences the efficiency of processing as well as fabric appearance. Lower unevenness generally results in a better-looking fabric but the relation is not simple and interpretation requires special care.

## 5 Apparatus

**5.1** Different types of apparatus are in use for measuring strands made of staple fibres and filament yarns.

**5.2** The apparatus consists of the following elements:

- a) measuring device, featuring
  - several measuring condensers, usually grouped into one unit, for strands of varying linear density,
  - yarn guiding and pretensioning devices,
  - an adjustable-speed motor to advance the strand;

- b) signal processing unit, which
- computes and indicates the values of  $CV_u$  or  $U_u$  and may also calculate the variance-length curve and present a graph of the periodic variations of linear density,
  - also counts the number of imperfections in most instruments. The unit shall be able to operate at the threshold level of + 50 %, above which thick places are counted, and the level of – 50 %, below which thin places are counted.
  - reports a reading for neps which shall be a product of the length, expressed in millimetres, of the nep and the percent excess over the average linear density of the yarn (for example, 4 mm × 50 %). The level of + 200 %, above which neps are counted, shall be available.
  - other levels (for the three imperfection types) are also usually available;
- c) printer (optional), which provides a plot of the linear density of the strand;
- d) twisting device for testing untwisted or low-twist filament yarns. This device produces false twist in an untwisted or low-twist filament yarn, so that the yarn presents a nearly round cross-section as it passes through the condenser. If the yarn passes through in a flat mode, there is the danger of adding variation depending on the way the flat yarn is presented. The direction of the imparted false twist must be the same as that of any twist present in the yarn. The twisting device need not be used for the testing of monofilaments.

**5.3** To calibrate, use the procedure built into the instrument if possible. Alternatively, use a standard (usually tape) of known unevenness provided by the instrument manufacturer and follow the manufacturer's instructions. Finally, if the manufacturer's standard is not available, an in-house material of known and preferably low unevenness, may be used.

## 6 Atmosphere for conditioning and testing

The standard atmosphere for preconditioning, conditioning and testing shall be as specified in ISO 139. Assure that the total length of the material to be tested is in moisture equilibrium. Conditioning for 24 h is usually sufficient for unsupported packages. Supported packages shall be conditioned for 48 h.

## 7 Sampling

**7.1** Select laboratory samples in one of the following two ways:

- according to a material specification, if available;
- by agreement between the parties.

**7.2** The following minimum numbers of packages are recommended:

- tops and slivers: 3 packages;
- rovings: 4 packages;
- staple-fibre yarns: 10 packages;
- filament yarns: 5 packages.

**7.3** The material shall be unwound directly from the package during testing so as to avoid possible deformation during handling.

**7.4** Test the number of specimens per package given in the material specification. If no specification is available, test one specimen per package.



**7.5** Test the following lengths of test specimens. These are minimum values for the total measured length.

- tops and slivers: 50 m;
- rovings: 100 m;
- staple-fibre yarns: 400 m;
- filament yarns: 400 m.

## **8 Procedure**

### **8.1 Setting of the apparatus**

If the tester allows a choice between a “normal” and an “inert” test, perform the “normal” test and then the “inert” if desired to establish the variance-length curve. The “normal” choice for some testers will result in the performance of both the “normal” and the “inert” tests automatically, so the setting can be to “normal”.

### **8.2 Setting of the diagram scale**

The following diagram scale settings are recommended for most cases:

- tops and slivers:  $\pm 25\%$ ;
- rovings:  $\pm 50\%$ ;
- glass-fibre rovings:  $\pm 100\%$ ;
- spun-fibre yarns:  $\pm 100\%$ ;
- filament yarns:  $\pm 10\%$  or  $12,5\%$ .

### **8.3 Selection of the condenser's measuring slot**

The measuring ranges of the neighbouring slots overlap to some extent, so that certain specimens can be tested in two slots, and the results may differ. Follow the instrument manufacturer's recommendation as to selection of slot for strands of a particular linear density.

### **8.4 Selection of running speed**

The following speeds are recommended. Other speeds may be used by agreement and shall then be stated in the test report.

- tops and slivers: 25 m/min;
- rovings: 50 m/min;
- yarns: 400 m/min.

### **8.5 Guiding facilities**

Before starting the test, adjust the guiding and tensioning devices to provide a pretension which does not extend or otherwise distort the material. The specimen needs to pass through the condenser without fluttering which would produce an error of measurement.

### **8.6 Twisting device**

Thread low-twist or untwisted filament yarns through the twisting device [see 5.2 d)].

## 8.7 Plot representing the linear density along the strand

Switch on the drive of the printer, if used. Only a short length of the plot will be needed.

## 8.8 Preliminary run

Old instruments may not stabilize their electronic measuring system automatically. In such cases, a preliminary run is recommended of approximately 20 % of the prescribed length.

## 8.9 Test run

Set the feed in motion and observe that the passage through the condenser is smooth and undisturbed. Run the test until the indicated  $CV_u$  or  $U_u$  value is stable, or for a specified time or length of strand, as mutually agreed.

## 9 Calculations and expression of results

**9.1** If several packages were tested with one reading for each package, calculate the average  $CV_u$  or  $U_u$  value and, if required, the coefficient of variation of the individual values and the 95 % confidence limits. Round all results to the nearest 0,1 %.

**9.2** If desired, determine the variance-length curve. If the instrument does not give the  $CV_u$  for long lengths, determine an additional  $CV_u$  for long-term unevenness by cutting and weighing, usually 100-m segments of yarn.

**9.3** Express the incidence of imperfections as the number per kilometre.

**9.3.1** Express the incidence of thick places as the number for which the linear density exceeds the average linear density of the yarn by at least 50 %. Counts at threshold levels other than + 50 %, if used, shall also be reported.

**9.3.2** Express the incidence of thin places as the number for which the linear density is less than 50 % of the average linear density of the yarn. Counts at threshold levels other than – 50 %, if used, shall also be reported.

**9.3.3** Express the incidence of neps as the number which exceeds a reading of + 200 % [see 5.2 b)]. Counts at a threshold reading of other than 200 %, if used, shall also be reported.

NOTE A reading of + 200 % is normally used for ring yarns and + 280 % for open-end yarns.

## 10 Test report

The test report shall include the following information:

- a) reference to this International Standard (ISO 16549:2004);
- b) date of the test;
- c) identification of the sample, including type of package;
- d) average unevenness value  $CV_u$  or  $U_u$ , in percent. If required, report also the individual results, their coefficient of variation and 95 % confidence limits;
- e) "length between",  $L_b$ , and "length within",  $L_w$ , if either differs from the usual values (see 4.4);
- f) graph of the variance-length curve, if determined;
- g) graph of the periodic variations, if determined;
- h) a short length of the plot of the linear density along the strand, if determined;
- i) number of thick places, if determined (see 9.3);
- j) number of thin places, if determined (see 9.3);

- k) number of neps, if determined (see 9.3);
- l) threshold for thick places if other than + 50 % (see 9.3.1);
- m) threshold for thin places if other than – 50 % (see 9.3.2);
- n) threshold for neps if other than + 200 % (see 9.3.3);
- o) running speed, if different from those given in 4.4;
- p) any deviation in procedure from this International Standard.

## Annex A (informative)

### Other methods for the determination of unevenness

#### A.1 Principles of test methods

There are three methods for evaluating unevenness:

- a) visual assessment;
- b) measuring devices which determine the variation of the mass of the material or other characteristics proportional to mass. Capacitance-type testers are covered in the body of this International Standard. Methods by squeezing are referred to in A.3.2;
- c) measuring devices which determine the variation of the diameter of the material or other characteristics proportional to diameter. Optical methods are referred to in A.4;
- d) since no exact ratio exists between mass and diameter, the results determined from methods A.1 b) and A.1 c) cannot be compared.

#### A.2 Visual assessment (suitable for yarns)

##### A.2.1 Yarn kept static and wound around a panel

The yarn is wound around a panel with specified winding density which depends on the linear density of the yarn. The panel can be rectangular or trapezoidal and should be of a contrasting colour. Trapezoidal panels highlight short periodical irregularities in the yarn by producing a moiré effect. The panels are assessed visually using agreed upon lighting. It may be helpful to tilt the panel during assessment.

For assessment use a comparison with standard materials or photographs. Alternatively, use agreed upon classification schemes or a verbal description of the observations.

For documentation, the panel with the wound yarn may be stored. Taking photographs is common. Placing photographic paper directly on the sample during lighting has been found to be helpful for avoiding eye irritation.

The visual method is simple to apply and is used quite often, despite the subjective assessment procedure. Image-analysed systems and storing-and-evaluation systems may be applied, if available.

##### A.2.2 Running yarn

Continuous unwinding and parallel grouping of rows of yarns allows visual observation of the running yarns by a test person, using appropriate lighting and a contrasting background. Verbal description of the observation is most often used and documentation of the test run is not possible.

#### A.3 Determination of mass

##### A.3.1 Cutting and weighing

This is a laborious and time-consuming method, used for special purposes such as evaluation of unevenness testers or research. The material is cut into segments of length  $L_b$  using appropriate equipment and the segments are weighed individually. The coefficient of variation of unevenness is calculated using the individual weights.

Note the following relationships.

- a) length of cut,  $L_b$ : As  $L_b$  increases, the value of unevenness decreases.
- b) number of packages: If segments of different packages are mixed, increased variation is expected. For example, when testing neighbouring yarns out of a warp (large number of packages), a higher variation results than for neighbouring yarns from a weft (small number of packages).
- c) order of segments: The cut segments may follow each other consecutively or not (at a regular or non-regular distance). A tendency to larger variation is observed using the non-regular distances; the results cannot be compared directly.

### **A.3.2 Method using squeezing (applicable mainly to tops and slivers)**

The strand is guided into a test area where it is squeezed against a steady bottom roller or plate by a movable measuring device. The movement of the measuring device is registered by mechanical or electrical means and is evaluated statistically.

### **A.4 Optical methods (suitable for yarns)**

The evaluation of the unevenness of yarn diameter using optical means is expected to produce an irregularity pattern similar to visual impression. The system is applied mainly to the control of filament yarns or for conductive and wet yarns.

The specimen is passed through an optical sensor (one or several systems of light sources and receivers). Optically distinguishable deviations of the diameter as detected by the system are registered by the receivers and can be evaluated statistically.

## Bibliography

- [1] ISO 2649:1974, *Wool — Determination of short-term irregularity of linear density of slivers, rovings and yarns, by means of an electronic evenness tester*
- [2] IWTO-18-00, *Method for the determination of evenness of textile strands using capacitance testing equipment*
- [3] BORNET, G.M. The Sigma unevenness tester and the checking of its accuracy by cutting and weighing, *J. Text. Inst.*, **56**, No. 9 (September 1965), pp. T465-476
- [4] Zellweger-Uster Co: "Uster Tester-4", *Theory and practice of unevenness testing* (copyright 2002)
- [5] Zellweger-Uster Co: "Uster Tester 4-CX", *Theory and practice of unevenness testing of filament yarns* (copyright 2002)







## ***SLS CERTIFICATION MARK***

*The Sri Lanka Standards Institution is the owner of the registered certification mark shown below. Beneath the mark, the number of the Sri Lanka Standard relevant to the product is indicated. This mark may be used only by those who have obtained permits under the SLS certification marks scheme. The presence of this mark on or in relation to a product conveys the assurance that they have been produced to comply with the requirements of the relevant Sri Lanka Standard under a well designed system of quality control inspection and testing operated by the manufacturer and supervised by the SLSI which includes surveillance inspection of the factory, testing of both factory and market samples.*

*Further particulars of the terms and conditions of the permit may be obtained from the Sri Lanka Standards Institution, 17, Victoria Place, Elvitigala Mawatha, Colombo 08.*



## **SRI LANKA STANDARDS INSTITUTION**

The Sri Lanka Standards Institution (SLSI) is the National Standards Organization of Sri Lanka established under the Sri Lanka Standards Institution Act No. 6 of 1984 which repealed and replaced the Bureau of Ceylon Standards Act No. 38 of 1964. The Institution functions under the Ministry of Science & Technology.

The principal objects of the Institution as set out in the Act are to prepare standards and promote their adoption, to provide facilities for examination and testing of products, to operate a Certification Marks Scheme, to certify the quality of products meant for local consumption or exports and to promote standardization and quality control by educational, consultancy and research activity.

The Institution is financed by Government grants, and by the income from the sale of its publications and other services offered for Industry and Business Sector. Financial and administrative control is vested in a Council appointed in accordance with the provisions of the Act.

The development and formulation of National Standards is carried out by Technical Experts and representatives of other interest groups, assisted by the permanent officers of the Institution. These Technical Committees are appointed under the purview of the Sectoral Committees which in turn are appointed by the Council. The Sectoral Committees give the final Technical approval for the Draft National Standards prior to the approval by the Council of the SLSI.

All members of the Technical and Sectoral Committees render their services in an honorary capacity. In this process the Institution endeavours to ensure adequate representation of all view points.

In the International field the Institution represents Sri Lanka in the International Organization for Standardization (ISO), and participates in such fields of standardization as are of special interest to Sri Lanka.