

SRI LANKA STANDARD 459:1979  
UDC 677.21:620.1

**METHOD FOR  
THE DETERMINATION OF MICRONAIRE  
VALUE OF COTTON FIBRES**

**BUREAU OF CEYLON STANDARDS**



METHOD FOR THE DETERMINATION OF  
MICRONAIRE VALUE OF  
COTTON FIBRES

SLS 459 : 1979

Gr. 5

*Copyright reserved*  
BUREAU OF CEYLON STANDARDS  
53, Dharmapala Mawatha,  
Colombo 3,  
Sri Lanka.



SRI LANKA STANDARD  
METHOD FOR THE DETERMINATION OF  
MICRONAIRE VALUE OF  
COTTON FIBRES

**FOREWORD**

This Sri Lanka Standard has been prepared by the Drafting Committee of the Bureau on Test Methods for Textiles. It was approved by the Textiles Divisional Committee of the Bureau of Ceylon Standards and was authorised for adoption and publication by the Council of the Bureau on 1979-08-03.

This standard is one of a series of Sri Lanka Standards on methods of test for textiles.

All standard values given in this method are in SI units.

This standard makes reference to the following standards.

CS 16 Standard atmospheres for conditioning and testing textiles.

SLS 360 Method of sampling raw cotton for testing.

This standard is based on ISO 2403:1972 issued by the International Organization for Standardization (ISO).

## 1 SCOPE AND FIELD OF APPLICATION

This Sri Lanka Standard specifies a method of determining the micronaire value of loose disoriented cotton fibres taken from bales, laps, and slivers, or other sources of lint cotton.

## 2 DEFINITION

**micronaire value:** A measure of the air permeability of a mass of cotton under specified conditions, expressed in terms of an arbitrary scale, the so-called micronaire scale. The micronaire scale is based on a range of cottons to which micronaire values have been assigned by international agreement.

## 3 PRINCIPLE

Air is passed through a test specimen consisting of a plug of fibres. The permeability is indicated on a scale for recording variations in either the rate of flow through, or the pressure difference across the plug. The mass and volume of the test specimen are either a constant for a given type of instrument or varied appropriately in relation to each other. The scale indicating variations in permeability may be calibrated in arbitrary units of micronaire value or marked in the appropriate absolute units of rate of flow or of pressure difference, and a table or graph provided for conversion of the observed readings into micronaire values.

## 4 APPARATUS AND MATERIALS

4.1 *Balance*, of sufficient capacity to weigh the test specimen required for the airflow instrument used, with an accuracy of  $\pm 0.2$  per cent.

4.2 *Airflow instrument*, whose principal parts are:

4.2.1 Compression cylinder with perforated ends of such dimensions that with the prescribed mass of specimen each cubic centimetre shall contain between 0.16g and 0.30g of cotton when compressed.

4.2.2 Means for measuring the air permeability of the specimen comprising, for example:

a) a suitable air pump;

b) one or more valves or other means for controlling the flow of air through, or the pressure difference across, the specimen in the compression cylinder; and

c) a manometer, for measuring the required air pressure difference across the specimen and a flowmeter for indicating the rate of airflow through it.

*NOTE - Details of certain commercially available instruments which comply with this specification are given in the Appendices of this Sri Lanka Standard. The method of calibration of airflow instruments is described in Appendix A.*

4.3 International calibration cotton standards,  
(See A.1 of Appendix A).

## 5 ATMOSPHERE FOR CONDITIONING AND TESTING

5.1 Condition test samples in the standard atmosphere for 4 hours in moving air (or alternatively for 12 hours in still air) or for a shorter time if the change in mass in a 2 hour period does not exceed 0.25 per cent before weighing and testing the specimen. Preconditioning is not required.

5.2 Weigh and test the specimen in the standard atmosphere for conditioning (Refer CS 16).

## 6 TEST SPECIMEN

6.1 Take test specimens in accordance with the instructions given in SLS 360 or specimens and samples may be drawn in other ways with prior agreement between the parties concerned.

6.2 Remove from the sample foreign bodies such as seed, sand, pieces of stalk and other impurities. Use a test specimen of the size prescribed for the instrument being used. In instruments having a compression cylinder of fixed volume, weigh the specimen to within  $\pm 0.2$  per cent of the specimen size appropriate for the instrument (See Appendices). In instruments having compression cylinders with adjustably varied volume, determine the mass of the specimen with an accuracy of  $\pm 0.2$  per cent.

6.3 Test the number of specimens per sample or per lot or shipment, and specify the scheme for the selection of samples, as agreed between the parties concerned.

## 7 PROCEDURE

7.1 Before each series of measurements make the necessary preliminary adjustments appropriate to the instrument in use (See Appendices). From time to time test a minimum of two check specimens from each three calibration cottons (See Appendix A) covering the range of micronaire values of samples to be tested to determine whether or not the instrument is correctly adjusted and is giving results on the correct level.



7.1.1 Consider the performance of any instrument to be within the requirements of this Sri Lanka Standard if the average results for each such calibration cotton do not differ from its corresponding established values by more than  $\pm 0.10$  micronaire scale unit.

7.1.2 Re-test, by the above procedure, cottons giving differences greater than  $\pm 0.10$  micronaire scale unit between the average of the two tests and the established value. Accept the results if the difference between the two new micronaire values for such a cotton does not exceed  $\pm 0.10$  micronaire scale unit. If the difference continues to be greater than  $\pm 0.10$  micronaire scale unit, either re-adjust the instrument and repeat the above, check procedure or apply, on the basis of the established differences referred to above, an appropriate correction or adjustment to test values for subsequent samples submitted for testing.

7.2 Pack the test specimen evenly into the compression cylinder, a small portion at a time, fluffing the fibres with the fingers in order to break up any lumps and taking care that all the fibres are inserted in the cylinder. Put the compression plunger in position and lock it.

7.3 Cause air to flow through the specimen at the appropriate flow (or pressure) and note the reading on the airflow (or pressure difference) scale of the instrument to an accuracy of about  $\pm 1$  per cent.

7.4 If a second measurement is required for the same specimen, remove the cotton from the instrument taking care not to lose fibre, and repeat the procedure given in 7.2 and 7.3.

## 8 CALCULATIONS AND EXPRESSION OF RESULTS

8.1 For instruments in which the scale is graduated in micronaire values, average the readings for the specimens tested from a sample. If necessary, apply any correction based on 7.1.2 and report the average to the nearest 0.1 micronaire value.

8.2 For instruments in which the scale is graduated in units other than micronaire values, convert the direct readings to micronaire values from a previously established conversion curve or statistical relation as described in Appendix A. Calculate the converted values as described in 8.1.

## 9 TEST REPORT

The test report shall include the following information:

- a) reference to this Sri Lanka Standard;
- b) the material source (lint, cotton, picker lap, processing waste) and if possible type and/or botanical species (for example: *Gossypium hirsutum*);
- c) the number of specimens tested, the number of readings per specimen, the number of samples used, and the scheme for drawing them;
- d) the average values calculated; and
- e) the type, make and model of instrument used.

## APPENDIX A

### METHOD OF CALIBRATION OF INSTRUMENTS

A.1 Calibration of airflow instruments is based on samples of a series of International Calibration Cottons which are available from the Standards Preparation and Distribution, Cotton Division, Consumer and Marketing Services, US Department of Agriculture, P.O. Box 17723, Memphis Tennessee, 38112 U.S.A. These are furnished with micronaire values established by the International Calibration Cotton Standards Committee.

A.2 For calibration purposes use the full range of calibration cottons available. They approximately cover the range of the micronaire values of the world's cottons.

*NOTE - The routine checking and adjusting of the instrument in relation to a section of the instrument's scale is to be distinguished from the more elaborate determination of the locations of numerous points along the full-scale range of the instrument when it is being calibrated. Routine checking for daily use is described in 7.1 to 7.1.2, B.2 and B.3 of Appendix B and in C.3 of Appendix C. Calibration of an instrument, such as at the factory, or upon receiving it at the laboratory, or occasionally under other special circumstances at the laboratory is described in the following Clauses of this Appendix.*

A.3 For each calibration cotton, make a minimum of two test determinations on each of the three test specimens. The difference between the test values for the first and second determinations shall not exceed 0.10 unit. If a greater difference is obtained, discard the result and make two determinations on a fresh test specimen. Take the average of the first readings on each of the three test specimens for each calibration cotton.

*NOTE - The scale from which the readings are noted may already be graduated in micronaire values (as with most commercially available instruments). For a new instrument it may be a uniformly graduated scale.*

A.4 For instruments already fitted with a scale, graduated in micronaire values, determine the difference between the average scale reading and the corresponding established value for each cotton. If none of these differences exceeds 0.10 unit, regard the previous calibration of the instrument as satisfactory. If greater differences occur, make appropriate instrument checks and adjustments to bring the instrument performance into compliance with the above requirements. Alternatively a series of appropriate scale corrections may be calculated.

A.5 For instruments fitted with a scale graduated in other than micronaire values, either:

plot a graph showing the average instrument readings as abscissae and the corresponding established values as ordinates and draw a smooth curve to pass evenly through the points.

or

determine statistically the relation between average instrument readings and corresponding established values in the form of an equation.

The deviations between average scale readings and established micronaire value shall not be greater than the equivalent of 0.01 unit, as indicated by the graph or by the statistically established relation, as in A.4.

A-6 Use the calibration curve, or the corresponding statistical relation, to convert final test values yielded by cotton samples into micronaire values. Alternatively fit the instrument with a scale graduated in micronaire values, the markings of which are obtained from the calibration curve or from the statistical relation.

## APPENDIX B

### METHOD OF OPERATION OF THE MICRONAIRE AIRFLOW INSTRUMENT\*

B-1 There are several models of the micronaire instrument. They vary only in details of construction and operation. Any details of the operation of a particular model which differ from the instructions given in this Appendix are described in the manufacturer's instructions included with the instrument.

#### B-2 Micronaire 60600

Mechanically adjust and check the instrument as follows:

- a) Adjust the primary air regulator to give a pressure of 172 kPa (1.76 kgf/cm<sup>2</sup>) and open the valve that admits air to the instrument. Check the reading after the air flows through the instrument, and make a re-adjustment if necessary.

---

\*Mention of the name of a specific or proprietary instrument is not intended to promote, or give preference to, the use of that instrument.

- b) Insert the manometer plug in the compression chamber. Allow the air to enter the chamber and adjust the secondary valve to obtain a pressure 41.4 kPa (0.42 kgf/cm<sup>2</sup>) in the compression chamber. Again if necessary, after the air flows through the instrument, re-adjust the regulating valve.
- c) Insert one of the master orifice plugs, allow the air to enter, and if necessary, turn the calibration screw to bring the float to the position on the curvilinear scale corresponding to the designation of the orifice plug. Repeat these operations, using the other orifice plug or disk.

#### NOTES

1 Instead of two calibration discs, each with its bore, one disc with two different bores may be used. If the latter is used, close one of the bores with a finger at the lower scale value (2.8), the bore to be closed being especially marked.

2 The scale readings 2.8 and 6.2 respectively correspond to flow rates of  $21.1 \pm 0.8$  l/min and  $49.3 \pm 1.4$  l/min.

#### B.3 Micronaire 80400

Mechanically adjust and check the instrument in accordance with 7.1 to 7.1.2 as follows:

- a) Operate the foot valve and see if the air pressure behind the filter is between 413 kPa (4.22 kgf/cm<sup>2</sup>) and 862 kPa (8.79 kgf/cm<sup>2</sup>).

- b) Open the pressure regulator and the upper and lower adjusting valves as far as possible.
- c) Insert the control disc in the test chamber and open the foot valve. Operate the pressure regulator so that the mercury column rises to 30.3 kPa(0.31 kgf/cm<sup>2</sup>). The air must pass through both bores of the control disc without hindrance. Operate the foot valve several consecutive times. The mercury must always rise to the same height.
- d) Adjust the lower adjusting valve so that the upper edge of the float comes to rest at micrometre value 4.6.
- e) Adjust the upper adjusting valve so that the upper edge of the float comes to rest at the upper check mark at about micrometre value 6.0.
- f) With one finger, tightly close the upper opening of the control disc. The float will then fall to about the level of the lower check mark.
- g) In order to make an exact adjustment, while alternately opening and shutting the upper opening of the control disc, alternately change the lower and upper adjusting valves. Do this until the upper edge of the float corresponds with the two check marks located at about micrometre values of 2.9 and 6.0.
- h) Turn the pressure regulator until the mercury column stands at 32.4 kPa(0.33 kgf/cm<sup>2</sup>).

- j) By opening and closing the upper opening of the control disc, check whether the upper and lower positions of the float still correspond with the two adjustment marks, even after the change of the mercury column from 30.3 kPa (0.31 kgf/cm<sup>2</sup>) to 32.4 kPa (0.33 kgf/cm<sup>2</sup>). If this does not occur, repeat the procedure in (g).
- k) Open and close the upper opening of the control disc several times. If the adjustments were correctly made, the float position must correspond to both marks without further changes of the adjusting valves.

*NOTE - If the manufacturer's instructions are different from those given above, adhere to the principles of these (standard) instructions as closely as possible.*

B.4 After a microneaire instrument has been mechanically adjusted (See B.2 and B.3) check the instrument with at least three international calibration cottons in accordance with 7.1 to 7.1.2. Repeat the checking with the calibration cottons at frequent intervals.

If it is necessary to calibrate the instrument, refer Appendix A.

B.5 Follow the instructions given in 5 and 6 of this Sri Lanka Standard for drawing, preparing and conditioning samples and specimens to be tested by airflow methods.

B.6 The test specimen for the various models of the microneaire instrument shall have a mass of 3.21g ± 6.48mg.



*NOTE - Weighing is a critical operation. The tolerances given are those which must be allowed for the balance. No additional tolerance is permitted for operator error.*

*B.7 Follow the instructions given in 7.2 to 7.4 of this Sri Lanka Standard for calculating and reporting results.*

## APPENDIX C

### METHOD OF OPERATION OF THE WIRA FINENESS METER (COTTON MODEL)\*

*C.1 There are two models of the Wira fineness meter (cotton model) described as the old model and new model respectively. They differ primarily in the scale units and size of test specimen used. The old model is graduated in litres per minute and measures a specimen having a mass of 6.0g. The new model is equipped with a scale graduated in micronaire values and measures a specimen having a mass of 5.0g.*

*C.2 For preliminary calibration, adjust the instrument until the level of the liquid in the manometer tube coincides with the upper zero mark.*

*NOTE- The lower edge of the meniscus is observed when noting the length of the liquid column.*

*For other details in preparing the instruments for use, refer the manufacturer's instructions which accompany the instrument.*

---

*\*Mention of the name of a specific or proprietary instrument is not intended to promote, or give preference to, the use of that instrument.*

C.3 After the instrument has been mechanically adjusted, check the instrument with at least three of the international calibration cotton standards, in accordance with 7.1 to 7.1.2. Repeat the check with calibration cottons at frequent intervals. If it is necessary to calibrate the instrument refer Appendix A.

C.4 Follow the instructions given in 5 and 6 of this Sri Lanka Standard for drawing, preparing and conditioning samples and specimens to be tested by airflow methods.

C.5 The test specimen for the old model Wira shall have a mass of  $6.0 \pm 0.012$  g and for the new model, it shall have a mass of  $5.0 \pm 0.01$  g.

C.6 Follow the instructions given in 7.2 to 7.4 of this Sri Lanka Standard for fluffing the specimen, loading and closing the compression cylinder, and reading the scale.

C.7 Follow the instructions given in 8 and 9 of this Sri Lanka Standard for calculating and reporting results.

## **SLS CERTIFICATION MARK**

*The Sri Lanka Standards Institution is the owner of the registered certification mark shown below. Beneath the mark, the number of the Sri Lanka Standard relevant to the product is indicated. This mark may be used only by those who have obtained permits under the SLS certification marks scheme. The presence of this mark on or in relation to a product conveys the assurance that they have been produced to comply with the requirements of the relevant Sri Lanka Standard under a well designed system of quality control inspection and testing operated by the manufacturer and supervised by the SLSI which includes surveillance inspection of the factory, testing of both factory and market samples.*

*Further particulars of the terms and conditions of the permit may be obtained from the Sri Lanka Standards Institution, 17, Victoria Place, Elvitigala Mawatha, Colombo 08.*



## **SRI LANKA STANDARDS INSTITUTION**

The Sri Lanka Standards Institution (SLSI) is the National Standards Organization of Sri Lanka established under the Sri Lanka Standards Institution Act No. 6 of 1984 which repealed and replaced the Bureau of Ceylon Standards Act No. 38 of 1964. The Institution functions under the Ministry of Science & Technology.

The principal objects of the Institution as set out in the Act are to prepare standards and promote their adoption, to provide facilities for examination and testing of products, to operate a Certification Marks Scheme, to certify the quality of products meant for local consumption or exports and to promote standardization and quality control by educational, consultancy and research activity.

The Institution is financed by Government grants, and by the income from the sale of its publications and other services offered for Industry and Business Sector. Financial and administrative control is vested in a Council appointed in accordance with the provisions of the Act.

The development and formulation of National Standards is carried out by Technical Experts and representatives of other interest groups, assisted by the permanent officers of the Institution. These Technical Committees are appointed under the purview of the Sectoral Committees which in turn are appointed by the Council. The Sectoral Committees give the final Technical approval for the Draft National Standards prior to the approval by the Council of the SLSI.

All members of the Technical and Sectoral Committees render their services in an honorary capacity. In this process the Institution endeavours to ensure adequate representation of all view points.

In the International field the Institution represents Sri Lanka in the International Organization for Standardization (ISO), and participates in such fields of standardization as are of special interest to Sri Lanka.