

මෙය රාජ්‍ය භාෂාවෙන් වෙනම මුද්‍රණය කර ඇත.

*Reaffirmed*  
2000

ලංකා ප්‍රමිති 59: 1969  
CEYLON STANDARD 59: 1969  
විශ්ව දශම වර්ග කිරීම UDC 667. 41: 686. 863. 6

*Reaffirmed*  
2008

උල්පත් (= පවුන්ටන්) පැන්වල භාවිතය සඳහා  
ගන්නා සේදිය හැකි නිල් තීන්ත පිළිබඳ ලංකා  
ප්‍රමිති පිරිවිතර

*Reaffirmed*  
2016

**Ceylon Standard Specification for washable  
blue-ink for fountain pens**

ලංකා ප්‍රමිති කාර්යාංශය  
BUREAU OF CEYLON STANDARDS

SPECIFICATION FOR WASHABLE BLUE-INK  
FOR FOUNTAIN PENS

C. S. 59: 1969  
(Attached AMD 261)

Gr.3  


*Copyright Reserved*  
BUREAU OF CEYLON STANDARDS  
53, Dharmapala Mawatha,  
COLOMBO 3.

**C. S. 59: 1969**

Ceylon Standards are subject to periodical revision in order to accommodate the progress made by industry. Suggestions for improvement will be recorded and brought to the notice of the Committees to which the revisions are entrusted.

This standard makes reference to the following Ceylon Standard

C. S. 33 - Specification for laundry soaps.

**BUREAU OF CEYLON STANDARDS**  
**53, Dharmapala Mawatha,**  
**Colombo 3.**

Telephone: 26051, 26054, 26055.

Telegrams: "PRAMIKA"

# CEYLON STANDARD SPECIFICATION FOR WASHABLE BLUE INK FOR FOUNTAIN PENS

## FOREWORD

This Ceylon Standard Specification has been prepared by the Drafting Committee on Writing Inks. It was approved by the Agricultural and Chemicals Divisional Committee of the Bureau of Ceylon Standards and was authorized for adoption and publication by the Council of the Bureau on 13th January, 1969.

This specification relates to washable blue ink suitable for use with fountain pens.

The publications of the British and Indian Standards Institutions have been of assistance in the preparation of this standard.

## 1. SCOPE

This specification prescribes the requirements and methods of test for washable blue ink for use with fountain pens.

## 2. DEFINITIONS

The term "washable" in connection with fountain pen inks means that they are capable of being washed from fabrics by the use of soap and water and **not** that they are fast to washing as the term is applied to dyed fabrics and paints.

## 3. REQUIREMENTS

The ink shall comply with the following requirements: (The composition of the standard reference ink shall be as given in the Appendix).

### 3.1 Composition

The blue dye content shall be sufficient to match the colour of the standard reference ink.

### 3.2 Corrosive action

Corrosive action of the ink shall be measured on brass and shall not exceed 3.5 per cent when tested as per method given in Sub-clause 6.1.

### 3.3 Freedom from sediment

The ink shall show no greater sediment than that of freshly prepared standard reference ink when tested by the method given in Sub-clause 6.2.