


SRI LANKA STANDARD 949 : PART 2 : 1992

UDC 669 . 14 . 018 - 426



SPECIFICATION FOR
DIMENSIONS OF HOT ROLLED STEEL BARS FOR
STRUCTURAL AND
GENERAL ENGINEERING PURPOSES
PART 2 - SQUARE BARS

SRI LANKA STANDARDS INSTITUTION

SPECIFICATION FOR DIMENSIONS OF HOT ROLLED STEEL BARS FOR
STRUCTURAL AND GENERAL ENGINEERING PURPOSES

PART 2 SQUARE BARS

SLS 949 : Part 2 : 1992
(Attached AMD 222)

Gr. 5

Copyright Reserved

SRI LANKA STANDARDS INSTITUTION

53, Dharmapala Mawatha,

Colombo 3,

Sri Lanka.

Sri Lanka Standards are subject to periodical revision in order to accommodate the progress made by industry. Suggestions for improvement will be recorded and brought to the notice of the Committees to which the revisions are entrusted.

This standard does not purport to include all the necessary provisions of a contract.

AMENDMENT NO. 01 APPROVED ON 1996-10-17 TO SLS 949 : PART 2 : 1992**SRI LANKA STANDARD SPECIFICATION FOR DIMENSIONS OF HOT ROLLED STEEL BARS FOR STRUCTURAL AND GENERAL ENGINEERING PURPOSES
PART 2 : SQUARE BARS****PAGE 1 AND PAGE 3****Title of Standard**

Delete the existing title of the standard and substitute the following:

**‘SPECIFICATION FOR HOT ROLLED STEEL BARS FOR STRUCTURAL AND GENERAL ENGINEERING PURPOSES
PART 2 - SQUARE BARS’**

PAGE 3**Clause 1 Scope**

Delete the contents and substitute the following:

“This standard specifies the requirements for chemical composition, manufacture, finish, mechanical properties, dimensions, marking, testing and sampling of hot rolled square steel bars used for structural and general engineering purposes”.

PAGE 7

TABLE 1 (b) - Dimensions, sectional area and mass per unit length (Second preference size)

Incorporate the following sizes after size 55 (width) given in Column 1 :

(1)	(2)	(3)
65	4225	33.2
75	5625	44.2

APPENDIX A

Sampling and criteria for conformity

The sampling and criteria for conformity of hot rolled square steel bars shall be in accordance with Appendix A of **SLS 1006 : Part 1 : 1993** or Appendix A of **SLS 1006 : Part 2 : 1993** as applicable”.

PAGE 9

Clause 6.3.6 Tolerance on twist

Incorporate the following after this clause:

“6.4 Chemical composition

The chemical composition of hot rolled square steel bars shall be in accordance with **6.1** of **SLS 1006 : Part 1 : 1993** or **6.1** of **SLS 1006 : Part 2 : 1993** as applicable.

6.5 Manufacture

The manufacture of hot rolled square steel bars shall be in accordance with **6.2** of **SLS 1006 : Part 1 : 1993** or **6.2** of **SLS 1006 : Part 2 : 1993** as applicable.

6.6 Finish

The finish of hot rolled square steel bars shall be in accordance with **6.3** of **SLS 1006 : Part 1 : 1993** or **6.3** of **SLS 1006 : Part 2 : 1993** as applicable

6.7 Mechanical Properties

The mechanical properties of hot rolled square steel bars shall be in accordance with **6.4** of **SLS 1006 : Part 1 : 1993** or **6.4** of **SLS 1006 : Part 2 : 1993** as applicable

7 MARKING

The marking of hot rolled square steel bars shall be in accordance with **7** of **SLS 1006 : Part 1 : 1993** or **7** of **SLS 1006 : Part 2 : 1993** as applicable

8 METHODS OF TEST

The methods of test of hot rolled square steel bars shall be in accordance with **8** of **SLS 1006 : Part 1 : 1993** or **8** of **SLS 1006 : Part 2 : 1993** as applicable

9 CERTIFICATE OF COMPLIANCE

The certificate of compliance of hot rolled square steel bars shall be in accordance with **9** of **SLS 1006 : Part 1 : 1993** or **9** of **SLS 1006 : Part 2 : 1993** as applicable

SRI LANKA STANDARD
SPECIFICATION FOR DIMENSIONS OF HOT ROLLED STEEL BARS FOR
STRUCTURAL AND GENERAL ENGINEERING PURPOSES

PART 2 . SQUARE BARS

FOREWORD

This standard was approved by the Sectoral Committee on Metal and Metal Products and was authorized for adoption and publication as a Sri Lanka Standard by the Council of the Sri Lanka Standards Institution on 92-01-20.

With the formulation of SLS 874 : 1989 Steel Products it became necessary to revise SLS 74 : 1969 Dimensions of round and square steel bars for structural and general engineering purposes and SLS 75 : 1969 Dimensions of steel flats for structural and general engineering purposes.

This standard is issued in five parts to meet that necessity and it supersedes SLS 74 : 1969 and SLS 75 : 1969.

The other parts of this standard are :

- Part 1 Round bars
- Part 3 Hexagonal bars
- Part 4 Octagonal bars
- Part 5 Flats

All values given in this standard are in SI units.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or an analysis shall be rounded off in accordance with SLS 102. The number of significant places retained in the rounded off value shall be the same as that of the specified value in this standard.

In the preparation of this standard, the assistance derived from the following publications is gratefully acknowledged.

- ISO 1035 : 1980 (E) Hot rolled steel bars
 - Part 2 Dimensions of square bars
 - Part 4 Tolerances
- BS 4449 : 1988 Carbon steel bar for the reinforcement of concrete

1 SCOPE

This standard specifies dimensions and tolerances of hot rolled square steel bars used for structural and general engineering purposes.

2 REFERENCES

- SLS 102 Presentation of numerical values
- SLS 874 Steel products
 - Part 1 Classification and definitions
 - Part 2 Identification markings

3 DEFINITIONS

For the purpose of this standard the following definition shall apply:

square bar : Finished product with uniform cross-section of sides, not less than 8 mm manufactured by hot rolling or forging and supplied as straight lengths.

4 SYMBOLS

The symbol used in this standard shall have the meaning assigned to it as given below.

b = width across flats of square bar (see Figure 1)

5 DESIGNATION

Square bars shall be designated by the word 'square' followed by the width of section in 'mm', as given below .

Square b

EXAMPLE :

Square 10 (see Table 1)

6 REQUIREMENTS

6.1 Dimensions

6.1.1 Dimensions shall be as given in Table 1(a) and Table 1(b) (see Fig. 1)

6.1.2 The corner radius shall be as given in Table 2.

6.2 Mass

The mass per metre length shall be as given in Table 1(a) and Table 1(b).




FIGURE 1 - Section of square bar

TABLE 1 (a) - Dimensions, sectional area and mass
per unit length
(Preferred size)

Width (b) mm (1)	Sectional area mm ² (2)	Mass per unit length kg/m (3)
8	64.0	0.502
10	100.0	0.785
12	144.0	1.13
14	196.0	1.54
16	256.0	2.01
18	324.0	2.54
20	400.0	3.14
22	484.0	3.80
25	625.0	4.91
30	900.0	7.06
35	1225.0	9.58
40	1600.0	12.6
50	2500.0	19.6
60	3600.0	28.3
70	4900.0	38.5
80	6400.0	50.2
100	10000.0	78.5
120	14400.0	113.0

NOTE

The values of mass are based on a density of steel of
7.85 kg/dm³.

TABLE 1 (b) Dimensions, sectional area and mass per unit length (Second preference size)

Width (b) mm (1)	Sectional area mm ² (2)	Mass per unit length kg/m (3)
28	784.0	6.15
32	1024.0	8.04
45	2025.0	15.9
55	3025.0	23.7
90	8100.0	63.6

NOTES

1. The values of mass are based on a density of steel of 7.85 kg/dm³.

2. Table 1 (a) gives the preferred sizes of square bars and Table 1 (b) gives the second preference sizes which should be ordered when it is not possible to use the sizes given in Table 1 (a).

TABLE 2 - Corner radius of square bars

Width across flats		Corner radius (max.)
Over mm (1)	Up to and including mm (2)	mm (3)
-	12	1.0
12	20	1.5
20	30	2.0
30	50	2.5
50	100	3.0
100	120	4.0

6.3 Tolerances

6.3.1 Tolerance on width

The tolerance on width shall be as given in Table 3.

TABLE 3 - Tolerance on width

Nominal width (b)		Tolerance or width mm (3)
Over mm (1)	Up to and including mm (2)	
	15	± 0.4
15	25	± 0.5
25	35	± 0.6
35	50	± 0.8
50	80	± 1.0
80	100	± 1.3
100	120	± 1.6
120	160	± 2.0
160	200	± 2.5
200	-	± 1.5% of width

6.3.2 Tolerance on length

Each bar shall be cut to a ± 25 mm of the length specified by the purchaser.

Where a minimum length is requested it shall be subject to a

tolerance of +50 mm.

-0

Where a maximum length is requested it shall be subject to a

tolerance of +0 mm.

-50

6.3.3 *Tolerance on mass*

The tolerance on mass shall be as given in Table 4.

TABLE 4 - Tolerance on mass

Nominal size mm (1)	Tolerance on mass per metre length in per cent (2)
8 and 10	± 6.5
12 and over	± 4.5

6.3.4 *Tolerance on squareness*

The permissible out-of-square for all sizes of square bars, measured as the difference of the distance between parallel faces of the same cross-section, shall be 75 per cent of the total tolerance specified on the nominal width of side in Table 3.

6.3.5 *Tolerance on straightness*

The tolerance on straightness shall be as given in Table 5.

TABLE 5 - Tolerance on straightness

Measurement over (1)	Tolerance on straightness (2)
Any one metre length	4.0 mm/m
The total length (1)	0.004 x l

6.3.6 *Tolerance on twist*

If twist tolerances are required by the purchaser, these shall be specified in the order. The method of measurement shall be agreed.

SLS CERTIFICATION MARK

The Sri Lanka Standards Institution is the owner of the registered certification mark shown below. Beneath the mark, the number of the Sri Lanka Standard relevant to the product is indicated. This mark may be used only by those who have obtained permits under the SLS certification marks scheme. The presence of this mark on or in relation to a product conveys the assurance that they have been produced to comply with the requirements of the relevant Sri Lanka Standard under a well designed system of quality control inspection and testing operated by the manufacturer and supervised by the SLSI which includes surveillance inspection of the factory, testing of both factory and market samples.

Further particulars of the terms and conditions of the permit may be obtained from the Sri Lanka Standards Institution, 17, Victoria Place, Elvitigala Mawatha, Colombo 08.



SRI LANKA STANDARDS INSTITUTION

The Sri Lanka Standards Institution (SLSI) is the National Standards Organization of Sri Lanka established under the Sri Lanka Standards Institution Act No. 6 of 1984 which repealed and replaced the Bureau of Ceylon Standards Act No. 38 of 1964. The Institution functions under the Ministry of Science & Technology.

The principal objects of the Institution as set out in the Act are to prepare standards and promote their adoption, to provide facilities for examination and testing of products, to operate a Certification Marks Scheme, to certify the quality of products meant for local consumption or exports and to promote standardization and quality control by educational, consultancy and research activity.

The Institution is financed by Government grants, and by the income from the sale of its publications and other services offered for Industry and Business Sector. Financial and administrative control is vested in a Council appointed in accordance with the provisions of the Act.

The development and formulation of National Standards is carried out by Technical Experts and representatives of other interest groups, assisted by the permanent officers of the Institution. These Technical Committees are appointed under the purview of the Sectoral Committees which in turn are appointed by the Council. The Sectoral Committees give the final Technical approval for the Draft National Standards prior to the approval by the Council of the SLSI.

All members of the Technical and Sectoral Committees render their services in an honorary capacity. In this process the Institution endeavours to ensure adequate representation of all view points.

In the International field the Institution represents Sri Lanka in the International Organization for Standardization (ISO), and participates in such fields of standardization as are of special interest to Sri Lanka.