

SRI LANKA STANDARD 1256 PART 25:2022
(ISO 2810:2020)
UDC 667.6

**METHOD OF TEST FOR
PAINTS AND VARNISHES
PART 25: GUIDANCE ON THE CONDUCT
OF NATURAL WEATHERING TESTS**
(First Revision)

SRI LANKA STANDARDS INSTITUTION

Sri Lanka Standard
METHOD OF TEST FOR PAINTS AND VARNISHES
PART 25: GUIDANCE ON THE CONDUCT OF NATURAL WEATHERING TESTS
(First Revision)

SLS 1256 Part 25:2022
(ISO 2810:2020)

Gr. G

Copyright Reserved
SRI LANKA STANDARDS INSTITUTION
17, Victoria Place
Elvitigala Mawatha
Colombo - 08
Sri Lanka.

Sri Lanka Standards are subject to periodical revision in order to accommodate the progress made by industry. Suggestions for improvement will be recorded and brought to the notice of the Committees to which the revisions are entrusted.

This Standard does not purport to include all the necessary provisions of a contract

© ISO 2020 - All right reserved.

© SLSI 2022

All right reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the SLSI

Sri Lanka Standard
METHODS OF TEST FOR PAINTS AND VARNISHES
PART 25: GUIDANCE ON THE CONDUCT OF NATURAL WEATHERING TESTS
(First Revision)

NATIONAL FOREWORD

This Standard was approved by the Sectoral Committee on Chemical and Polymer Technology and authorized for adoption and publication as a Sri Lanka Standard by the Council of the Sri Lanka Standards Institution on 2022-09-25

This Sri Lanka Standard is the First Revision to SLS 1256 Part 25 which was an adoption of ISO 2810:2004 Methods of test for paints and varnishes Part 25: Guidance on the conduct of natural weathering tests. The text of the above International Standard has been technically revised as ISO 2810:2020 Paints and varnishes - Natural weathering of coatings - Exposure and assessment. The International Standard ISO 2810:2020 has been accepted for adoption as the First Revision of SLS 1256 Part 25:2022

This Sri Lanka Standard is identical with ISO 2810:2020 Paints and varnishes - Natural weathering of coatings - Exposure and assessment, published by the International Organization for Standardization (ISO).

TERMINOLOGY AND CONVENTIONS

The text of the International Standard has been accepted as suitable for publication, without deviation, as a Sri Lanka Standard. However, certain terminology and conventions are not identical with those used in Sri Lanka Standards. Attention is therefore drawn to the following:

- a) Wherever the words “International Standard” appear referring to a particular Standard they should be interpreted as “Sri Lanka Standard”.
- b) The comma has been used throughout as a decimal marker. In Sri Lanka Standards it is the current practice to use the full point at the base as the decimal marker.
- c) Wherever page numbers are quoted, they are ISO page numbers.

CROSS REFERENCES

International Standard

Corresponding Sri Lanka Standard

ISO 1514, Paints and varnishes - Standard panels for testing

SLS 1256 Part 40:2017 Methods of test for paints and varnishes - Preparation of standard panels for testing (panels other than burnished steel, glass, wood and asbestos)

ISO 2808, Paints and varnishes - Determination of film thickness

SLS 1256 Part 15:2008 Methods of test for paints and varnishes - Determination of film thickness

ISO 4618, Paints and varnishes - Terms and definitions

SLS 1541:2016 Terms and definitions for paints and varnishes

.....

INTERNATIONAL
STANDARD

ISO
2810

Third edition
2020-09

**Paints and varnishes — Natural
weathering of coatings — Exposure
and assessment**

*Peintures et vernis — Vieillessement naturel des revêtements —
Exposition et évaluation*



Reference number
ISO 2810:2020(E)

© ISO 2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 General	1
5 Exposure racks	2
6 Apparatus for measurement of climatic factors	3
6.1 Measurement of solar radiation.....	3
6.1.1 Pyranometers.....	3
6.1.2 Pyrheliometers.....	3
6.1.3 Total-ultraviolet radiometers.....	4
6.1.4 Narrow-band ultraviolet radiometers.....	4
6.2 Other climate-measuring instruments.....	4
7 Test specimens	4
8 Procedure	5
9 Supplementary test conditions	5
10 Evaluation of properties	6
11 Precision	6
12 Test report	6
Annex A (normative) Environment and climate	8
Annex B (informative) Classification of climates	10
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 139, *Paints and varnishes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 2810:2004), which has been technically revised. The main changes compared to the previous edition are as follows:

- in [Clause 4](#), the list in b) has been amended by radiant exposure and temperature;
- the time of wetness has been deleted from the list of additional observations on climate in [A.2](#) and replaced by a note with the reference to ASTM Practice G84;
- the climate classification in [Annex B](#) has been updated to ISO 877-1:2009;
- the text has been editorially revised and the normative references have been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Paints and varnishes — Natural weathering of coatings — Exposure and assessment

1 Scope

This document specifies the conditions to take into consideration when selecting the type of natural weathering and the natural weathering procedure to determine the resistance of coatings or coating systems (direct weathering or weathering behind window glass).

Natural weathering is used to determine the resistance of coatings or coating systems (denoted in this document by coatings) to the sun's radiation and the atmosphere.

This document does not take into account special atmospheric influences, e.g. industrial pollution.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 4618, *Paints and varnishes — Terms and definitions*

WMO Publication No, 8, *Guide to meteorological instruments and methods of observation*, World Meteorological Organization, Geneva, 2012

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

durability

ability of a specimen to resist the deleterious effect of its environment

3.2

time of wetness

period during which an exposed coating has surface moisture present on it

4 General

The durability of a coating during natural weathering depends on how, where and when the coating is weathered. Therefore, these parameters and the intended use of the coating shall be taken into account when exposures are carried out.

In particular, the following parameters shall be considered:

- a) the location of the exposure site, for example industrial, marine, rural; in choosing sites, those which differ markedly in the type or level of pollution from the normal shall be avoided, unless they are appropriate to the intended end use of the coating under test;
- b) the height, angle and orientation of the exposure rack; these parameters govern the extent to which the specimens are affected, for example by radiant exposure, temperature, dew, frost and atmospheric pollutants;
- c) the nature of the terrain on which the rack is constructed (for example concrete, grass, gravel); the terrain may affect the climatic conditions around the specimen under test; it would rarely be feasible to select an ideal terrain in practice, but the effect of such variations in climatic conditions will be minimized by ensuring that all specimens are situated sufficiently high above the ground (see [Clause 5](#));
- d) whether the performance of the coating on the front and/or the back of the specimen is of interest; certain types of degradation, for example rust formation and/or mould growth, are frequently more severe on the shaded parts of the specimen;
- e) the intended use of the coating, including its substrate, and whether the coating is to be washed or polished in service.

The results of tests on an exposure rack apply precisely only to the environment in which they were obtained.

Provided that the test conditions are reasonably appropriate to the intended end use, the relative performance of a number of coatings tested at the same time enables valid deductions to be drawn. It is recommended that each series of specimens under evaluation include coatings of known performance to act as reference standards.

The results of natural weathering may vary according to the time of year during which the tests are carried out. The influence of these variations is reduced if the exposure period is sufficiently long. The exposure period should be at least one year, or a multiple of one year. The reproducibility of the results is improved if the exposure period always starts at the same time of year, preferably in spring.

Natural weathering tests are normally carried out for a fixed period of time. However, in many cases it is preferable to define the test period in terms of a certain degree of degradation or by the radiant exposure (dosage) of solar radiation to which the specimen is to be subjected (see [Clause 6](#)). The latter procedure can reduce the influence of seasonal variations but does not eliminate it.

Radiant exposure can be determined by measurement of irradiance, and integration of the measurements over the period of natural weathering.

The climatic conditions shall be monitored, and a complete record shall be reported, together with the other conditions of weathering.

Care is required in the selection of test specimens of substrates with variable (anisotropic) properties, for example wood or steel. In these cases, replication of the tests is essential to avoid misleading results.

Washing and polishing during exposure affects the durability of the coating. It shall therefore be mentioned in the test report.

5 Exposure racks

Unless otherwise specified or agreed, use exposure racks on which the specimens are facing towards the equator. The specimens shall be firmly held on the racks by attachments made of stainless steel or other corrosion-resistant material, in such a manner that they are mechanically stressed as little as possible.

The exposure racks shall be constructed so that the atmosphere has free access to the specimens and that water that drains from one specimen does not drain onto another. In addition, the racks can be designed so that a portion of the specimens can be covered to allow evaluation between an exposed and a masked area. By using special devices, particular conditions may be simulated, for example by using a “black box” in accordance with SAE J 1976 to simulate automotive conditions or backing the test panel with plywood or other insulation material to simulate building side wall or roof area conditions.

Metal substrates for corrosion tests shall not be in electrical contact with metals during the exposure period or, as far as possible, in direct contact with wood or other porous materials. If specimens are supported in grooves, suitable drainage holes shall be provided to prevent accumulation of water.

Unless otherwise stated, the racks shall be constructed so that all specimens are supported either at a minimum height of 0,45 m above the ground or at a height sufficient to avoid contact with vegetation and to prevent damage.

The area beneath and in the vicinity of the racks shall be characterized by low reflectance and by ground cover typical of that climatological area. In desert areas, the racks shall be located on gravel, in most temperate areas on low-cut grass.

Usually the panels are supported at an angle of 45° to the horizontal. Depending on the intended end use of the coating, other angles may be agreed, for example 5° for automotive finishes or roof coatings, or vertical exposure for textured wall finishes.

NOTE When testing corrosion performance, it is appropriate to expose specimens vertically facing away from the equator as well as inclined at 45° and 5° facing towards the equator (see EN 13523-19).

Specimens facing away from the equator will remain wet for longer periods since they dry less rapidly than those exposed facing towards the equator. This leads to a higher tendency to corrode.

The racks shall be situated so that, at a sun height of 20° and more, no shadow falls on to the specimens.

When testing the durability of coatings for interior use which are exposed to radiation which has passed through window glass, racks that are covered by a window pane are used. Since, depending on the quality, the transmission of window glass in the UV range is different, the type of window glass shall be agreed upon between the interested parties for each particular case (see [Clause 9](#)).

6 Apparatus for measurement of climatic factors

6.1 Measurement of solar radiation

6.1.1 Pyranometers

Pyranometers are radiometers used to measure the total solar radiant energy incident upon a surface per unit time per unit area.

The energy measured includes direct and diffuse radiant energy as well as radiant energy reflected from the background.

Pyranometers shall meet at least the requirements for a second class instrument as defined by the World Meteorological Organization (WMO), WMO Publication No. 8. In addition, pyranometers shall be calibrated at least annually, and their calibration factor shall be traceable to the World Radiometric Reference (WRR) WMO Publication No. 8, Chapter 9.

6.1.2 Pyrhemometers

Pyrhemometers are radiometers used to measure the direct (beam) solar irradiance incident on a surface normal to the sun's rays.

The energy measured excludes diffuse radiant energy as well as radiant energy reflected from the background.

Pyrheliometers shall meet at least the requirements for a first class instrument as defined by the WMO Publication No. 8. In addition, pyrheliometers shall be calibrated at least annually, and their calibration factor shall be traceable to the WRR WMO Publication No. 8.

6.1.3 Total-ultraviolet radiometers

When used to define exposure stages, total-ultraviolet radiometers shall have a passband that maximizes the acceptance of radiation in the 300 nm to 400 nm, 295 nm to 385 nm, or any other commonly used total-ultraviolet wavelength region, and they shall be cosine-corrected to include ultraviolet sky radiation. Commercially available total-ultraviolet radiometers require annual calibration checks if they are deployed between latitudes 40° north and 40° south. Outside these latitudes, annual calibration is not a requirement but it is considered good practice.

6.1.4 Narrow-band ultraviolet radiometers

When used to define exposure stages, narrow-band ultraviolet radiometers shall be cosine-corrected if used in conjunction with either natural fixed-angle or glass-filtered exposures. They shall be calibrated following the manufacturer's instructions.

6.2 Other climate-measuring instruments

Instrumentation required for the measurement of air temperature, specimen surface temperature, relative humidity, rainfall, time of wetness, and sunshine hours shall be appropriate to the exposure method used and shall be agreed upon between the interested parties.

7 Test specimens

The simplest and most widely used test specimen is a flat panel of the appropriate substrate, but much useful additional information can be obtained by carrying out exposure tests on structures. This is particularly true of wooden assemblies such as window frames, where coating performance at the joints is of interest. Design features which allow accumulation and entrapment of water can also lead to premature coating degradation. Therefore, test specimens should preferably be included which show the characteristics of such structures.

Unless otherwise agreed, use standard test panels in accordance with ISO 1514, with the area of the panels at least 0,03 m² and no side less than 100 mm long.

Coat the panels with the product(s) under test by the appropriate method and dry (or stove) each coat in the specified manner for the specified time, followed (if appropriate) by conditioning or ageing. Coat both faces and the edges of the panels with the product under test, unless the panel would not be used in such manner. Alternatively, the back and edges may be coated with a good-quality protective paint [see [Clause 4](#), d)].

If specified or agreed, particularly in the case of corrosion tests, provide uncoated areas on the specimen, preferably by one or more of the following methods.

- a) After the specified drying time and immediately before placing the specimens on the exposure rack, make a straight scratch or scribe mark through the coating to the substrate. To make the scratch, use an instrument with a hard tip. The scratch shall have a width of 0,2 mm to 1,0 mm, unless otherwise agreed. As the result of the test depends on, e.g. the depth of the scratch and the scratching tool used, the details of how the scratch was made shall be stated in the test report.

NOTE Normally, vertical and/or horizontal lines are used. By agreement, diagonal criss-cross lines (a St. Andrew's cross) can be employed. However, in this case, the coating might flake where the lines cross which makes evaluation, e.g. by image analysis, difficult.

- b) Before applying the product(s) under test, attach to the prepared specimen a strip of pressure-sensitive adhesive tape of agreed size at an agreed location. Coat the specimen in the normal way. Either directly after coating or immediately before placing on the exposure rack, carefully remove the tape. Clean off any residues of adhesive with a suitable solvent which does not affect the coating.

Determine the thickness, in micrometres, of the coating by using one of the non-destructive methods specified in ISO 2808. Provide the specimens with a suitable marking which is resistant to natural weathering.

The number of test specimens depends on

- the number of different properties to be investigated and the number of specimens required for each test method, and
- the number of times each test method is to be carried out before, during and after weathering.

If not otherwise specified or agreed, the number of test specimens shall be not less than three.

The use of reference specimens of known durability and of composition similar to that of the test specimen is recommended.

8 Procedure

After any conditioning or specified pre-aging, expose the specimens on the rack for the specified time or until the specified level of radiant exposure has been reached or until a defined degree of degradation is reached.

If specified, wash all or part of the specimen at the required intervals. If only part of the specimen is to be washed, it is preferable to wash a strip on the right or left of the specimen, rather than at the top or bottom. It can also be necessary to define exactly the particular area to be washed. When the specimen-washing procedure is not specified in detail, use water in accordance with ISO 3696, grade 3, to which a suitable wetting agent has been added. Apply the washing solution with a soft brush or soft sponge, subsequently rinsing the surface thoroughly with water of grade 3, avoiding mechanical damage.

If specified, wash and polish all or part of each specimen at the required intervals, using the specified polish.

Examine the specimens at defined intervals, separately noting the resistance of the coating on the front, back, edges or bare areas. Examinations shall be at intervals appropriate to the rate of degradation, for example for change of colour, for loss of gloss, for blistering of the coating and for signs of corrosion of the substrate. If specified, also examine with $\times 10$ magnification for cracking, blistering of the coating and for signs of corrosion of the substrate. Examine for signs of chalking by pressing and rotating (or wiping) a piece of velvet of contrasting colour over the surface, for example in accordance with the method described in ISO 4628-7.

After the specified period of exposure, carry out a final examination of the coating. If it is required to examine the substrate for signs of attack, remove the coating by the specified method.

9 Supplementary test conditions

For any particular application of the test method specified in this document, more details, in addition to those in the preceding clauses, might be required.

To enable the method to be carried out, the following test conditions shall be laid down as appropriate:

- a) the material, the thickness and the surface preparation of the substrate;
- b) the method of application of the coating materials under test to the substrate;

- c) the duration and conditions of drying (or stoving) and ageing (if applicable) of the coating, the intervals between coats and the period of conditioning before exposure;
- d) the thickness, in micrometres, of the dry coating and the method of measurement in accordance with ISO 2808, and whether it is a single coating or a multicoat system;
- e) whether bare areas are to be provided on the specimen and, if so, their size and position and by what means they are to be made;
- f) details of any periodic washing or polishing procedure to be carried out during the course of exposure;
- g) any particular requirements regarding the exposure location;
- h) the duration of the test;
- i) which properties of the coating are to be evaluated prior to, during and after exposure, and the standards to be used;
- j) where requested, the method of removal of the coating from the substrate;
- k) if used, the transmittance characteristics of the glass, if measured, and thickness (all interested parties should agree upon the wavelengths at which transmittance is reported).

These test conditions should preferably be agreed between the interested parties and can be derived, in part or totally, from an international or national standard or other document related to the product under test.

10 Evaluation of properties

Measure the specified or agreed properties of the coating (see [Clause 9](#)) prior to, during and after the exposure, e.g. in accordance with ISO 2813, ISO 3668, ISO 4628-1, ISO 4628-2, ISO 4628-3, ISO 4628-4, ISO 4628-5, ISO 4628-6, ISO 4628-8, ISO 4628-10 and/or ISO 18314-1.

11 Precision

The principle of repeatability and reproducibility is not applicable to this document. However, experience has shown that for test specimens exposed under the same test parameters at the same exposure site a comparable ranking of products can be obtained.

12 Test report

The test report shall contain at least the following information:

- a) all information necessary for complete identification of the product tested;
- b) a reference to this document, i.e. ISO 2810:2020
- c) the supplementary test conditions referred to in [Clause 9](#);
- d) a reference to the international or national standard, product specification or other document supplying the information referred to in c);
- e) the weathering procedure used (direct weathering or weathering behind window glass);
- f) the test details:
 - 1) exposure aspect (for example tilt and azimuth orientation);

- 2) location and details of exposure site (e.g. longitude, latitude, altitude, annual climate characteristics);
- 3) class and type of climate (examples are shown in [Annex B](#), reference in test report if used);
- 4) nature of masking, backing, support and attachments, if used;
- 5) procedure used to determine the exposure stages;
- 6) exposure stages:
 - i) starting time;
 - ii) elapsed time (weeks, months, years);
 - iii) total solar radiant exposure, expressed in joules per square metre, including the method used to measure it, if it is measured (see [6.1](#)).
- 7) details of washing procedure, if specified (see [Clause 8](#));
- g) details of the scratch, if made, and of the tool used to make it;
- h) the test results as indicated in [Clause 10](#), including
 - 1) the intervals between removal of specimen from rack and property measurement, and
 - 2) climatological data as specified in [Annex A](#);
- i) any items which were agreed between the interested parties;
- j) any deviation from the weathering procedure specified;
- k) any unusual features (anomalies) observed during the test;
- l) the date of the test.

Annex A (normative)

Environment and climate

A.1 Classification of environment and climate

A.1.1 Environment

A classification of environments, used especially to describe the environmental impact on steel structures, is given in ISO 12944-2 (which is based on ISO 9223). For general requirements for atmospheric corrosion field tests, including requirements for monitoring, see ISO 8565:1992, Clause 3.

Marine and industrial influences are likely to have a significant impact on the basic climatic conditions of a region. These particular conditions are referred to as the microclimate of the test site. In coastal regions, where the atmosphere can contain traces of salt but is generally otherwise clean, exposed specimens receive more solar radiation and are likely to degrade more rapidly than in comparable inland regions.

NOTE Certain coatings are known to degrade more rapidly in desert exposure sites than in coastal test sites.

In industrial areas, atmospheric pollution and dirt retained on the specimens reduce the effect of solar radiation, although the pollution and dirt can at the same time make the effects of moisture more pronounced.

A.2 Climate

Climates are divided into classes, each subdivided into several types. [Annex B](#) gives details of one such classification in use throughout the world. The classification is such that significant differences are to be expected between each class with respect to its effect on the weathering behaviour of paints.

A.3 Additional observations on climate

The general description of the climate at the exposure site by class, type and special conditions should preferably be supplemented by the following detailed observations.

- a) Temperature:
 - 1) monthly mean of daily maxima;
 - 2) monthly mean of daily minima;
 - 3) monthly maximum and minimum.
- b) Relative humidity:
 - 1) monthly mean of daily maxima;
 - 2) monthly mean of daily minima;
 - 3) monthly maximum and minimum.
- c) Precipitation:
 - 1) total monthly rainfall, in millimetres;

2) total monthly time of wetness, in hours.

NOTE ASTM Practice G84 describes a procedure for determination of time of wetness. Other procedures can be used if mutually agreed upon by interested parties.

d) Other observations:

Other observations, such as wind speed and direction, incidence and nature of any atmospheric pollution, total ultraviolet radiant exposure (if measured) and any special local features, can also be recorded.

Annex B **(informative)**

Classification of climates

The most widely recognized system for defining and classifying the various types of climate is based on the work of German climatologist Wladimir Köppen who introduced this climate classification system in 1928 and published modifications and improvements until he died in 1940. Köppen's classification system was originally developed for vegetation and has been modified by several researchers, but the most common modification in use today was developed by Glenn Trewartha of the University of Wisconsin in the USA. A full description of Trewartha's modification of Köppen's climate classification is described in Reference [20]. In this system, climates are classified into six basic types. Within each of the basic types, there are several different subtypes based on temperature and precipitation. These are described in [Table B.1](#).

NOTE This information is taken from ISO 877-1:2009, Table A.1.

Table B.1 — Climate classification and description

Climate type	Name of climate type	Climate subtype	Name of climate/subclimate	General description	Average temperature
A	Tropical humid	Af	Tropical wet	No dry season	>17 °C all year
		Am	Tropical monsoonal	Short dry season; heavy monsoon rain in other month	
B	Dry	Aw	Tropical savanna	Winter dry season	
		BWh	Subtropical desert	Low-latitude desert	Not applicable (for type B climates, evaporation exceeds precipitation). The temperature of type B climates is indicated by the third letter. A "h" is used for climates where the coldest month has an average temperature greater than 0 °C. A "k" indicates that at least one month has an average temperature of less than 0 °C.
		BSh	Subtropical steppe	Low-latitude dry	
		BWk	Mid-latitude desert	Mid-latitude desert	
		BSk	Mid-latitude steppe	Mid-latitude dry	
C	Mild mid-latitude	Csa	Mediterranean	Mild with dry, hot summer	
		Csb	Mediterranean	Mild with dry, warm summer	
		Cfa	Humid subtropical	Mild with no dry season, hot summer	
		Cwa	Humid subtropical	Mild with dry winter, hot summer	>9 °C for 8 months to 12 months
		Cfb	Marine west coast	Mild with no dry season, warm summer	
		Cfc	Marine west coast	Mild with no dry season, cool summer	
		Dfa	Humid continental	Humid with severe winter, no dry season, hot summer	
		Dfb	Humid continental	Humid with severe winter, no dry season, warm summer	>9 °C for 4 months to 7 months
		Dwa	Humid continental	Humid with severe, dry winter, hot summer	
		Dwb	Humid continental	Humid with severe, dry winter, warm summer	
D	Severe mid-latitude	Dfc	Subarctic	Severe winter, no dry season, cool summer	
		Dfd	Subarctic	Severe, very cold winter, no dry season, cool summer	
		Dwc	Subarctic	Severe, dry winter, cool summer	> 9 °C for 1 month to 3 months
		Dwd	Subarctic	Severe, very cold and dry winter, cool summer	
		ET	Tundra	Polar tundra, no true summer	No month with average temperature >9 °C
		EF	Ice cap	Perennial ice	
H	Undifferentiated highlands	H	Undifferentiated highlands	High altitude	Not applicable

Bibliography

- [1] ISO 877-1:2009, *Plastics — Methods of exposure to solar radiation — Part 1: General guidance*
- [2] ISO 2813, *Paints and varnishes — Determination of gloss value at 20°, 60° and 85°*
- [3] ISO 3668, *Paints and varnishes — Visual comparison of colour of paints*
- [4] ISO 4628-1, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 1: General introduction and designation system*
- [5] ISO 4628-2, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering*
- [6] ISO 4628-3, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 3: Assessment of degree of rusting*
- [7] ISO 4628-4, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 4: Assessment of degree of cracking*
- [8] ISO 4628-5, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 5: Assessment of degree of flaking*
- [9] ISO 4628-6, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 6: Assessment of degree of chalking by tape method*
- [10] ISO 4628-7, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 7: Assessment of degree of chalking by velvet method*
- [11] ISO 4628-8, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 8: Assessment of degree of delamination and corrosion around a scribe or other artificial defect*
- [12] ISO 4628-10, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 10: Assessment of degree of filiform corrosion*
- [13] ISO 8565:1992, *Metals and alloys — Atmospheric corrosion testing — General requirements for field tests*
- [14] ISO 9223, *Corrosion of metals and alloys — Corrosivity of atmospheres — Classification, determination and estimation*
- [15] ISO 12944-2, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 2: Classification of environments*
- [16] ISO 18314-1, *Analytical colorimetry — Part 1: Practical colour measurement*
- [17] ASTM G84, *Standard Practice for Measurement of Time-of-Wetness on Surfaces Exposed to Wetting Conditions as in Atmospheric Corrosion Testing*
- [18] EN 13523-19, *Coil coated metals — Test methods — Part 19: Panel design and method of atmospheric exposure testing*

- [19] SAE J 1976, *Outdoor weathering of exterior materials*
- [20] TREWARTHA G.A., *Introduction to Climate*. McGraw-Hill, New York, USA, Fifth Edition, 1980

SLS CERTIFICATION MARK

The Sri Lanka Standards Institution is the owner of the registered certification mark shown below. Beneath the mark, the number of the Sri Lanka Standard relevant to the product is indicated. This mark may be used only by those who have obtained permits under the SLS certification marks scheme. The presence of this mark on or in relation to a product conveys the assurance that they have been produced to comply with the requirements of the relevant Sri Lanka Standard under a well designed system of quality control inspection and testing operated by the manufacturer and supervised by the SLSI which includes surveillance inspection of the factory, testing of both factory and market samples.

Further particulars of the terms and conditions of the permit may be obtained from the Sri Lanka Standards Institution, 17, Victoria Place, Elvitigala Mawatha, Colombo 08.



SRI LANKA STANDARDS INSTITUTION

The Sri Lanka Standards Institution (SLSI) is the National Standards Organization of Sri Lanka established under the Sri Lanka Standards Institution Act No. 6 of 1984 which repealed and replaced the Bureau of Ceylon Standards Act No. 38 of 1964. The Institution functions under the Ministry of Technology.

The principal objects of the Institution as set out in the Act are to prepare standards and promote their adoption, to provide facilities for examination and testing of products, to operate a Certification Marks Scheme, to certify the quality of products meant for local consumption or exports and to promote standardization and quality control by educational, consultancy and research activity.

The Institution is financed by Government grants, and by the income from the sale of its publications and other services offered for Industry and Business Sector. Financial and administrative control is vested in a Council appointed in accordance with the provisions of the Act.

The development and formulation of National Standards is carried out by Technical Experts and representatives of other interest groups, assisted by the permanent officers of the Institution. These Technical Committees are appointed under the purview of the Sectoral Committees which in turn are appointed by the Council. The Sectoral Committees give the final Technical approval for the Draft National Standards prior to the approval by the Council of the SLSI.

All members of the Technical and Sectoral Committees render their services in an honorary capacity. In this process the Institution endeavours to ensure adequate representation of all view points.

In the International field the Institution represents Sri Lanka in the International Organization for Standardization (ISO), and participates in such fields of standardization as are of special interest to Sri Lanka.