

මෙය රාජ්‍ය භාෂාවෙන් වෙනම මුද්‍රණය කර ඇත.

ශ්‍රී ලංකා ප්‍රමිති 360 : 1975

SRI LANKA STANDARD 360 : 1975

විෂව දශම වර්ග කිරීම UDC 677.01

**පරීක්ෂා කිරීම සඳහා අමුසපු කෙඳි
නියැදීමේ ක්‍රමය පිළිබඳ පිරිවිතර**

**STANDARD ON METHOD OF
SAMPLING RAW COTTON
FOR TESTING**

**ලංකා ප්‍රමිති කාර්යාංශය
BUREAU OF CEYLON STANDARDS**

**STANDARD ON METHOD OF SAMPLING
RAW COTTON FOR TESTING**

S.L.S. 360 : 1975

Gr. 2

~~Retained~~

Copyright Reserved
BUREAU OF CEYLON STANDARDS
53, DHARMAPALA MAWATHA,
COLOMBO-3.

S.L.S. 360 : 1975

Sri Lanka Standards are subject to periodical revision in order to accommodate the progress made by industry. Suggestions for improvement will be recorded and brought to the notice of the Committees to which the revisions are entrusted.

This Standard does not purport to include all the necessary provisions of a contract.

BUREAU OF CEYLON STANDARDS
53, DHARMAPALA MAWATHA
COLOMBO 3.

Telephone: 26055
26054
26051

Telegrams: "PRAMIKA"

SRI LANKA STANDARD ON METHOD OF SAMPLING RAW COTTON FOR TESTING

FOREWORD

This Sri Lanka Standard was adopted from the ISO Recommendation R 220 under the authority of the Textiles Divisional Committee of the Bureau of Ceylon Standards, and was authorised for publication by the Council of the Bureau on 5th November 1975.

The quality of cotton textile products depend on the various properties of raw cotton fibre used. In order to determine these properties it is necessary to obtain a representative sample so that there is no variation from one part to another. However, it is not possible for this standard to be completely comprehensive and the selection of test samples must necessarily be covered by the appropriate specification for a given method of test.

1. SCOPE

- 1.1 A procedure is indicated for sampling raw cotton fibre for the purpose of determining its various properties.
- 1.2 The various stages of sampling, intended to reduce the quantity of cotton to be handled at different levels of the bulk to be tested, are described.
- 1.3 Special methods of sampling may be given in specifications or contracts for cotton, when the nature of the materials or other circumstances make them desirable.

2. DEFINITIONS

- 2.1 **Bulk source**—One or more bales of cotton, for example:
 - (a) a bale,
 - (b) a group of bales of one variety,
 - (c) a group of bales of a particular grade,
 - (d) a group of bales from a given area,
 - (e) a group of bales of a particular blend or a mix at the mill.

- 2.2 Laboratory bulk sample**—That portion of cotton taken from the bulk source in such a way as to ensure its representative character and to provide a quantity small enough to be handled with ease in the laboratory.
- 2.3 Laboratory test sample**—That portion of cotton fibres taken from the laboratory bulk sample in such a way as to ensure its representative character and to provide a quantity small enough to be easily convertible into test specimens.
- 2.4 Test specimen**—That portion of cotton fibres taken from the laboratory test sample which is to be placed in the testing machine at one time in order to determine a particular property.

3. PRINCIPLE

A laboratory bulk sample is taken from the bulk source, A laboratory test sample is taken from the laboratory bulk sample, and one or more test specimens are taken from the laboratory test sample. Each of these stages is intended to reduce the quantity of cotton, while preserving as far as possible its representativeness of the bulk source of cotton to be tested. All these stages may be used to advantage, but one or more may be omitted if this proves desirable.

4. LABORATORY BULK SAMPLE

The laboratory bulk sample should be taken in accordance with the requirements of contracts or in another way so that it should be duly representative.

Notes

1. To obtain a composite sample that will be small enough to be easily handled in the laboratory, it is suggested that a total of at least 100 g (4 oz) of cotton should be taken. Since the bulk source is usually heterogeneous as regards the properties of the fibres, it is very important that it should be represented as perfectly as possible in the laboratory bulk sample. To bring this about with the least possible alteration of fibre properties, carry out all the operations of extracting and preparing the sample with the most scrupulous care.
2. Representativeness is of very great importance with so variable a material as cotton. Too much time and effort can hardly ever be spent in securing representativeness throughout the sampling process.

5. LABORATORY TEST SAMPLE

- 5.1** The laboratory test sample should be prepared by a method which takes into consideration the test to be performed and the degree of accuracy desired.
- 5.1.1** In general, fibre blending by a mechanical blender is preferable, particularly when the test specimen is small in size, as is the case in the flat-bundle strength test. However in some cases, samples prepared by hand are adequate.
- 5.1.2** When the laboratory bulk sample consists of tufts taken by cutting into the bales, cut fibres should not be included in the laboratory test sample.
- 5.2** Mechanical blending (preferred method)
- 5.2.1** The mechanical blender is designed to use a certain weight of fibres, e.g. up to 10 g. ($\frac{1}{2}$ oz.).
- 5.2.2** Spread out the laboratory bulk sample so that pinches can be taken from it at any point. Take small pinches of fibre from at least 32 different evenly spaced points in the laboratory bulk sample.
- 5.2.3** Perform a light drafting action on the pinches before feeding them into the mechanical blender, so as to form as uniform a sheet of fibre as possible. Blend the fibres with the blender so as to produce a practically homogeneous sample, taking care not to damage the fibres.
- 5.3** Manual methods
- 5.3.1** Different methods have been described in national standards. They are designed for different methods of test, e.g. "cut-squaring", making hand slivers and making small samples by successive halving and combining. In some cases, it is preferable to prepare test specimens direct from the laboratory bulk sample.

6. TEST SPECIMEN

Prepare the test specimen according to the procedure described in the appropriate method of test.

BUREAU OF CEYLON STANDARDS

The Bureau of Ceylon Standards (BCS) is the national standards organisation of Sri Lanka and was established by the Hon. Minister of Industries & Fisheries, as provided for by the Bureau of Ceylon Standards Act, No. 38 of 1964.

The principal objects of the Bureau as set out in the Act are to promote standards in industry and commerce, prepare national Standard Specifications and Codes of Practice and operate a Standardisation Marks Scheme and provide testing facilities, as the need arises.

The Bureau is financed by Government grants and the sale of its publications. Financial and administrative control is vested in a Council appointed in accordance with the provisions of the Act.

The detailed preparation of Standard Specifications is done by Drafting Committees composed of experts in each particular field assisted by permanent officers of the Bureau. These Committees are appointed by Divisional Committees, which are appointed by the Council. All members of the Drafting and Divisional Committees render their services in an honorary capacity. In preparing the Standard Specifications, the Bureau endeavours to ensure adequate representation of all view points.

In the International field the Bureau represents Sri Lanka in the International Organisation for Standardisation (ISO) and will participate in such fields of Standardisation as are of special interest to Sri Lanka.