

SRI LANKA STANDARD 101 : 1986

U D C 677 . 21 . 06 : 687 . 11

**SPECIFICATION FOR
COTTON SARONGS (HANDLOOM)
(FIRST REVISION)**

SRI LANKA STANDARDS INSTITUTION

SPECIFICATION FOR COTTON SARONGS (HANDLOOM)
(FIRST REVISION)

SLS 101:1986

Gr. 5

Copyright Reserved

SRI LANKA STANDARDS INSTITUTION

53, Dharmapala Mawatha,

Colombo 3,

Sri Lanka.

SRI LANKA STANDARD
SPECIFICATION FOR COTTON SARONGS (HANDLOOM)
(FIRST REVISION)

FOREWORD

This Sri Lanka Standard was authorized for adoption and publication by the Council of the Sri Lanka Standards Institution on 1986-12-17, after the draft, finalized by the Drafting Committee on Cotton Sarongs, had been approved by the Textiles Divisional Committee.

This specification was first published in 1971. It consisted of two parts namely,

Part 1 - Cotton sarongs (Handloom)

Part 2 - Cotton sarongs (Powerloom)

Since powerloom cotton sarongs are not manufactured at present in Sri Lanka, in this revision, Part 2 of the earlier specification has been deleted.

Some commonly used constructional details for handloom cotton sarongs are given in Appendix A as a guidance to the manufacturers, taking into consideration the different types of sarongs available in the market. Minimum values have been specified for breaking strength, and mass per unit area. Requirements for Colour fastness to dry and wet rubbing has been introduced while requirements for colour fastness to bleaching and perspiration have been deleted.

All standard values given in this specification are in SI units.

For the purpose of deciding whether a particular requirement of this specification is complied with, the final value, observed or calculated, expressing the results of a test or analysis, shall be rounded off in accordance with CS 102. The number of significant places retained in the rounded off value should be the same as that of the specified value in this specification.

In the preparation of this specification, valuable assistance derived from related publications of the Indian Standards Institution is gratefully acknowledged.

1 SCOPE

This specification prescribes requirements, methods of sampling and tests for handloom cotton sarongs.

2 REFERENCES

- SLS 41 Determination of the number of threads per centimetre in woven fabrics (First revision)
- CS 42 Determination of mass per unit length and per unit area of woven or knitted fabrics
- CS 43 Determination of breaking load and extension of strips of woven textile fabric
- CS 44 Determination of the count of yarn removed from fabric, free from added matter
- SLS 45 Determination of length of woven fabric (First revision)
- SLS 46 Determination of width of woven fabric (First revision)
- CS 47 Method for shrinkage of fabrics - cold water immersion test
- CS 55 Determination of colour fastness of textile materials to washing at 95 °C for 30 minutes (Test 4)
- CS 62 Determination of colour fastness of textile materials to daylight
- CS 63 Determination of colour fastness of textile materials to rubbing
- CS 86 Determination of pH value of aqueous extracts of textile materials
- CS 87 Determination of scouring loss in grey and finished cotton textile materials
- CS 89 Determination of bow and skewness in woven fabric
- CS 102 Presentation of numerical values
- SLS 137 Grey cotton yarn
Part 2 - Handloom (First revision)
- SLS 428 Random sampling methods

3 REQUIREMENTS

3.1 General requirements

3.1.1 Yarn

3.1.1.1 Cotton yarn conforming to SLS 137:Part 2 is suitable for use in the manufacture of the cloth.

3.1.2 Cloth

3.1.2.1 The cloth shall be of plain weave.

3.1.2.2 The cloth when visually examined, shall be reasonably free from defects.